




Europäisches
Patentamt

European
Patent Office

PCT/EP03/11634
10/531779
Rec'd PCT/PTO
Office européen
des brevets
19 APR 2005



Bescheinigung

Certificate

Attestation

Die angehefteten Unterla-
gen stimmen mit der
ursprünglich eingereichten
Fassung der auf dem näch-
sten Blatt bezeichneten
europäischen Patentanmel-
dung überein.

The attached documents
are exact copies of the
European patent application
described on the following
page, as originally filed.

Les documents fixés à
cette attestation sont
conformes à la version
initialement déposée de
la demande de brevet
européen spécifiée à la
page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

03101113.3

**PRIORITY
DOCUMENT**
SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

Der Präsident des Europäischen Patentamts;
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets
p.o.

R C van Dijk

BEST AVAILABLE COPY



Anmeldung Nr:
Application no.: 03101113.3
Demande no:

Anmeldetag:
Date of filing: 23.04.03
Date de dépôt:

Anmelder/Applicant(s)/Demandeur(s):

Ciba Specialty Chemicals Holding Inc.
Klybeckstrasse 141
4002 Basel
SUISSE

Bezeichnung der Erfindung/Title of the invention/Titre de l'invention:
(Falls die Bezeichnung der Erfindung nicht angegeben ist, siehe Beschreibung.
If no title is shown please refer to the description.
Si aucun titre n'est indiqué se référer à la description.)

Novel Polymers for Use in Optical Devices

In Anspruch genommene Priorität(en) / Priority(ies) claimed / Priorité(s)
revendiquée(s)
Staat/Tag/Aktenzeichen/State/Date/File no./Pays/Date/Numéro de dépôt:

Internationale Patentklassifikation/International Patent Classification/
Classification internationale des brevets:

G02B1/04


Am Anmeldetag benannte Vertragstaaten/Contracting states designated at date of
filing/Etats contractants désignées lors du dépôt:

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IT LU MC NL
PT RO SE SI SK TR LI

Novel Polymers for Use in Optical Devices

The present invention relates to novel polymers comprising pyrimidine containing repeating units and to their use in optical devices, such as an optical device comprising an electroluminescent device or a photovoltaic device.


Derivatives of poly(p-phenylenevinylene) have been known for some time as electroluminescence (EL) materials (see, for example, WO90/13148).




WO98/11150 discloses triazine polymers of formula and their use in
electroluminescence (EL) arrangements.

WO00/46321 and US-B-6,512,083 relate to fluorene-containing polymers and their use in EL arrangements.


EP-A-690052 discloses the use of pyrimidine containing conjugated compounds, such as for

example , as
electroluminescent materials.



WO02/059121 discloses monomers having formula , wherein X is O,
S, NR, RC-CR, or RC=CR, Ar is an aryl or heteroaryl group, and E is a reactive group
capable of undergoing chain extension and their use for the production of polymers which
can be used in optical devices (see also WO01/62869).

DE-A-19651439 (US-A-6,323,373) relates to polymerizable biaryl derivatives of the formula



where the symbols and indices have the following meanings:

X: $-\text{CH}_2\text{-Z}$, $-\text{CHO}$;

Y^1 , Y^2 , Y^3 : CH; N,

5 Z: identical or different, I, Cl, Br, CN, SCN, NCO, $\text{PO}(\text{OR}^1)_2$, $\text{PO}(\text{R}^2)_2$, $\text{P}(\text{R}^3)_3^+ \text{A}^-$;

Aryl: an aryl group having from 6 to 14 carbon atoms;

R^1 , R'' : identical or different, CN, F, Cl, a straight-chain or branched or cyclic alkyl or alkoxy group having from 1 to 20 carbon atoms, where one or more nonadjacent CH_2 groups is optionally replaced by $-\text{O}-$, $-\text{S}-$, $-\text{CO}-$, $-\text{COO}-$, $-\text{O}-\text{CO}-$, $-\text{NR}^4-$, $-(\text{NR}^5\text{R}^6)^+ \text{A}^-$ or $-\text{CONR}^7-$ and

10 one or more H atoms is optionally replaced by F, or an aryl group having from 6 to 14 carbon atoms which may be substituted by one or more nonaromatic radicals R' ;

R^1 , R^2 , R^3 , R^5 , R^6 : identical or different, aliphatic or aromatic hydrocarbon radicals having from 1 to 20 carbon atoms;

R^4 , R^7 : identical or different, hydrogen or aliphatic or aromatic hydrocarbon radicals having

15 from 1 to 20 carbon atoms;

A^- : a singly charged anion or its equivalent;

m: 0, 1 or 2;

n: 1, 2, 3, 4 or 5 and their use for the production of polymers.

20 There are a number of challenges faced with the introduction of organic EL displays when their performance is compared with existing technologies. Obtaining the exact color coordinates required by specific guidelines (i.e. NTSC) has been problematic. The operational lifetime of the EL device is relatively lower when contrasted to the existing inorganic technology. In addition, producing a material with a pure blue color and a long

25 lifetime is one of the greatest problems for this industry.


Accordingly, it is the object of the present invention to provide novel materials, which show significant advantages in color-purity, device-efficiency and/or operational lifetime, when incorporated in optical devices.

Said object is solved by the polymers of the present invention comprising diazine, especially pyrimidine, containing repeating units. Optical devices, comprising the polymers of the present invention, can show significant advantages in color purity, device efficiency and/or operational lifetime. In addition, the polymers can have good solubility characteristics and relatively high glass transition temperatures, which facilitates their fabrication into coatings and films that are relatively thin, thermally stable, and relatively free of defects. If the polymers contain end groups which are capable of being crosslinked, the crosslinking of such groups after the films or coating is formed increases the solvent resistance thereof, which is beneficial in applications wherein one or more solvent-based layers of material are deposited thereon.

Accordingly, the polymers of the present invention should have a glass transition temperature above 100°C, especially a glass transition temperature above 150°C.


As used herein the term "polymer of the present invention" refers to polymers having repeating units of formula I, including formula Ia and Ib, and/or II, including formula IIa, IIb and IIc.

In a first aspect, the present invention relates to polymers comprising a repeating unit of the formula




(I), wherein R^1 and R^2 are independently of each other an organic substituent, especially C_6 - C_{30} aryl or a C_2 - C_{26} heteroaryl, which optionally can be substituted,

X^1 and X^2 are independently of each other a divalent linking group, wherein repeating units of






(Ia), or




(Ib) are preferred.


Examples of suitable divalent linking groups X^1 and X^2 are a single bond, -CO-, -COO-; -S-; -SO-; -SO₂-; -O-; -CR²³=CR²⁴-; or -C≡C-; especially

4



5





$n_1, n_2, n_3, n_4, n_5, n_6$ and n_7 are integers of 1 to 10, in particular 1 to 3,


R^6 and R^7 are independently of each other H, C_1 - C_{18} alkyl, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D, C_6 - C_{24} aryl, C_6 - C_{24} aryl which is substituted by E, C_2 - C_{20} heteroaryl, C_2 - C_{20} heteroaryl which is substituted by E, C_2 - C_{18} alkenyl, C_2 - C_{18} alkynyl, C_1 - C_{18} alkoxy, C_1 - C_{18} alkoxy which is substituted by E and/or interrupted by D, C_7 - C_{25} aralkyl, or $-CO-R^{28}$, R^8 is C_1 - C_{18} alkyl, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D, C_6 - C_{24} aryl, or C_7 - C_{25} aralkyl,

R^9 and R^{10} are independently of each other C_1 - C_{18} alkyl, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D, C_6 - C_{24} aryl, C_6 - C_{24} aryl which is substituted by E, C_2 - C_{20} heteroaryl, C_2 - C_{20} heteroaryl which is substituted by E, C_2 - C_{18} alkenyl, C_2 - C_{18} alkynyl, C_1 - C_{18} alkoxy, C_1 - C_{18} alkoxy which is substituted by E and/or interrupted by D, or C_7 - C_{25} aralkyl, or R^9 and R^{10} form a ring, especially a five- or six-membered ring,


$R^{14'}$ and $R^{15'}$ are independently of each other H, C_1 - C_{18} alkyl, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D, C_6 - C_{24} aryl, C_6 - C_{24} aryl which is substituted by E, C_2 - C_{20} heteroaryl, or C_2 - C_{20} heteroaryl which is substituted by E, D is $-CO-$; $-COO-$; $-S-$; $-SO-$; $-SO_2-$; $-O-$; $-NR^{25}-$; $-SiR^{30}R^{31}-$; $-POR^{32}-$; $-CR^{23}=CR^{24}-$; or $-C\equiv C-$; and

E is $-OR^{29}$; $-SR^{29}$; $-NR^{25}R^{26}$; $-COR^{28}$; $-COOR^{27}$; $-CONR^{25}R^{26}$; $-CN$; $-OCOOR^{27}$; or halogen; wherein

R^{23} , R^{24} , R^{25} and R^{26} are independently of each other H; C_6 - C_{18} aryl; C_6 - C_{18} aryl which is substituted by C_1 - C_{18} alkyl, C_1 - C_{18} alkoxy; C_1 - C_{18} alkyl; or C_1 - C_{18} alkyl which is interrupted by $-O-$; or



R^{25} and R^{26} together form a five or six membered ring, in particular



R^{27} and R^{28} are independently of each other H; C_6-C_{18} aryl; C_6-C_{18} aryl which is substituted by C_1-C_{18} alkyl, or C_1-C_{18} alkoxy; C_1-C_{18} alkyl; or C_1-C_{18} alkyl which is interrupted by $-O-$,

5 R^{29} is H; C_6-C_{18} aryl; C_6-C_{18} aryl, which is substituted by C_1-C_{18} alkyl, C_1-C_{18} alkoxy; C_1-C_{18} alkyl; or C_1-C_{18} alkyl which is interrupted by $-O-$,

R^{30} and R^{31} are independently of each other C_1-C_{18} alkyl, C_6-C_{18} aryl, or C_6-C_{18} aryl, which is substituted by C_1-C_{18} alkyl, and

R^{32} is C_1-C_{18} alkyl, C_6-C_{18} aryl, or C_6-C_{18} aryl, which is substituted by C_1-C_{18} alkyl.

10

Preferably, R^6 and R^7 are independently of each other H, C_1-C_{18} alkyl, such as methyl, ethyl, n-propyl, iso-propyl, n-butyl, isobutyl, sec-butyl, t-butyl, 2-methylbutyl, n-pentyl, isopentyl, n-hexyl, 2-ethylhexyl, or n-heptyl, C_1-C_{18} alkyl which is substituted by E and/or interrupted by D, such as $-CH_2OCH_3$, $-CH_2OCH_2CH_3$, $-CH_2OCH_2CH_2OCH_3$, or $-CH_2OCH_2CH_2OCH_2CH_3$, C_6-

15 C_{24} aryl, such as phenyl, naphthyl, or biphenyl, C_6-C_{24} aryl which is substituted by E, such as $-C_6H_4OCH_3$, $-C_6H_4OCH_2CH_3$, $-C_6H_3(OCH_3)_2$, or $-C_6H_3(OCH_2CH_3)_2$, $-C_6H_4CH_3$, $-C_6H_3(CH_3)_2$, $-C_6H_2(CH_3)_3$, or $-C_6H_4tBu$.

20 R^8 is preferably H, C_1-C_{18} alkyl, such as methyl, ethyl, n-propyl, iso-propyl, n-butyl, isobutyl, sec-butyl, t-butyl, 2-methylbutyl, n-pentyl, isopentyl, n-hexyl, 2-ethylhexyl, n-heptyl, or C_6-C_{24} aryl, such as phenyl, naphthyl, or biphenyl.

25 Preferably, R^9 and R^{10} are independently of each other H, C_1-C_{18} alkyl, such as n-butyl, sec-butyl, hexyl, octyl, or 2-ethyl-hexyl, C_1-C_{18} alkyl which is substituted by E and/or interrupted by D, such as $-CH_2(OCH_2CH_2)_wOCH_3$, $w = 1, 2, 3$, or 4 , C_6-C_{24} aryl, such as phenyl, naphthyl, or biphenyl, C_6-C_{24} aryl which is substituted by E, such as $-C_6H_4OCH_3$, $-C_6H_4OCH_2CH_3$, $-C_6H_3(OCH_3)_2$, $-C_6H_3(OCH_2CH_3)_2$, $-C_6H_4CH_3$, $-C_6H_3(CH_3)_2$, $-C_6H_2(CH_3)_3$, or $-C_6H_4tBu$, or R^9 and R^{10} together form a 4 to 8 membered ring, especially a 5 or 6 membered ring, such as cyclohexyl, or cyclopentyl.


Preferably, $R^{14'}$ and $R^{15'}$ are independently of each other H, C_1 - C_{18} alkyl, such as methyl, ethyl, n-propyl, iso-propyl, n-butyl, isobutyl, or sec-butyl, or C_6 - C_{24} aryl, such as phenyl, naphthyl, or biphenyl.

5

D is preferably $-\text{CO}-$, $-\text{COO}-$, $-\text{S}-$, $-\text{SO}-$, $-\text{SO}_2-$, $-\text{O}-$, $-\text{NR}^{25}-$, wherein R^{25} is C_1 - C_{18} alkyl, such as methyl, ethyl, n-propyl, iso-propyl, n-butyl, isobutyl, or sec-butyl, or C_6 - C_{24} aryl, such as phenyl, naphthyl, or biphenyl.

10 E is preferably $-\text{OR}^{29}$; $-\text{SR}^{29}$; $-\text{NR}^{25}\text{R}^{25}$; $-\text{COR}^{28}$; $-\text{COOR}^{27}$; $-\text{CONR}^{25}\text{R}^{25}$; or $-\text{CN}$; wherein R^{25} , R^{27} , R^{28} and R^{29} are independently of each other C_1 - C_{18} alkyl, such as methyl, ethyl, n-propyl, iso-propyl, n-butyl, isobutyl, sec-butyl, hexyl, octyl, or 2-ethyl-hexyl, or C_6 - C_{24} aryl, such as phenyl, naphthyl, or biphenyl.








15 Among the above-mentioned groups X^1 and X^2 the following groups are preferred:



substituents are defined as above.


20 R^1 and R^2 can in principal be any organic substituent, provided he does not have negative influence on the (electro)luminescent characteristics of the polymers. Examples of R^1 and R^2 are: C_1 - C_{18} alkyl, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D, C_2 - C_{18} alkynyl, C_1 - C_{18} alkoxy, C_1 - C_{18} alkoxy which is substituted by E and/or interrupted by D, C_7 - C_{25} aralkyl, C_6 - C_{24} aryl, or C_2 - C_{20} heteroaryl, which optionally can be


25 substituted, especially a group of the formula





wherein m1, m2, m3, m4, m5, m6 and m7 are integers of 1 to 10, in particular 1 to 3,

X⁶ is H, C₁-C₁₈alkyl, C₁-C₁₈alkyl which is substituted by E and/or interrupted by D, C₆-C₂₄aryl,






, C₂-C₂₀heteroaryl, which optionally can be substituted, especially



, or



, C₂-C₁₈alkenyl, C₂-C₁₈alkynyl, C₁-C₁₈alkoxy,

C₁-C₁₈alkoxy which is substituted by E and/or interrupted by D, or C₇-C₂₅aralkyl,

X⁴ is C₁-C₁₈alkyl, C₁-C₁₈alkyl which is substituted by E and/or interrupted by D, C₆-C₂₄aryl,

5 which optionally can be substituted,

X⁵ is C₁-C₁₈alkyl, C₆-C₂₄aryl, C₆-C₂₄aryl substituted by -OC₁-C₁₈alkyl or -OC₆-C₂₄aryl,

R¹¹, R¹² and R¹³ are independently of each other H, C₁-C₁₈ alkyl, C₁-C₁₈alkyl which is

substituted by E and/or interrupted by D, C₆-C₂₄aryl, C₆-C₂₄aryl which is substituted by E, C₂-

C₁₈alkenyl, C₂-C₁₈alkynyl, C₁-C₁₈alkoxy, C₁-C₁₈alkoxy which is substituted by E and/or

10 interrupted by D, C₇-C₂₅aralkyl, and

D, E, R⁶, R⁷, R⁸, R⁹, R¹⁰, R¹⁴ and R¹⁵ are as defined above.

Preferably, R⁶ and R⁷ are independently of each other H, C₁-C₁₈ alkyl, such as methyl, ethyl,

n-propyl, iso-propyl, n-butyl, isobutyl, sec-butyl, t-butyl, 2-methylbutyl, n-pentyl, isopentyl, n-

15 hexyl, 2-ethylhexyl, or n-heptyl, C₁-C₁₈alkyl which is substituted by E and/or interrupted by D,

such as -CH₂OCH₃, -CH₂OCH₂CH₃, -CH₂OCH₂CH₂OCH₃, or -CH₂OCH₂CH₂OCH₂CH₃, C₆-

C₂₄aryl, such as phenyl, naphthyl, or biphenyl, C₆-C₂₄aryl which is substituted by E, such as

-C₆H₄OCH₃, -C₆H₄OCH₂CH₃, -C₆H₃(OCH₃)₂, or -C₆H₃(OCH₂CH₃)₂, -C₆H₄CH₃, -C₆H₃(CH₃)₂,

-C₆H₂(CH₃)₃, or -C₆H₄tBu.

20

R⁸ is preferably H, C₁-C₁₈alkyl, such as methyl, ethyl, n-propyl, iso-propyl, n-butyl, isobutyl,

sec-butyl, t-butyl, 2-methylbutyl, n-pentyl, isopentyl, n-hexyl, 2-ethylhexyl, and n-heptyl, or

C₆-C₂₄aryl, such as phenyl, naphthyl, or biphenyl.

25 Preferably, R⁹ and R¹⁰ are independently of each other H, C₁-C₁₈alkyl, such as n-butyl, sec-

butyl, hexyl, octyl, and 2-ethyl-hexyl, C₁-C₁₈alkyl which is substituted by E and/or interrupted

by D, such as -CH₂(OCH₂CH₂)_wOCH₃, w = 1, 2, 3, or 4, C₆-C₂₄aryl, such as phenyl, naphthyl,

and biphenyl, C₆-C₂₄aryl which is substituted by E, such as -C₆H₄OCH₃, -C₆H₄OCH₂CH₃,

-C₆H₃(OCH₃)₂, -C₆H₃(OCH₂CH₃)₂, -C₆H₄CH₃, -C₆H₃(CH₃)₂, -C₆H₂(CH₃)₃, and -C₆H₄tBu, or R⁹

30 and R¹⁰ together form a 4 to 8 membered ring, especially a 5 or 6 membered ring, such as cyclohexyl, or cyclopentyl.

Preferably, $R^{14'}$ and $R^{15'}$ are independently of each other H, C_1 - C_{18} alkyl, such as methyl, ethyl, n-propyl, iso-propyl, n-butyl, isobutyl, and sec-butyl, or C_6 - C_{24} aryl, such as phenyl, naphthyl, and biphenyl.

5

X^4 is preferably C_1 - C_{18} alkyl, such as methyl, ethyl, n-propyl, iso-propyl, n-butyl, isobutyl, sec-butyl, t-butyl, hexyl, octyl, and 2-ethyl-hexyl, or C_6 - C_{24} aryl, such as phenyl, naphthyl, and biphenyl, and X^5 is preferably C_1 - C_{18} alkyl, such as methyl, ethyl, n-propyl, iso-propyl, n-butyl, isobutyl, sec-butyl, t-butyl, hexyl, octyl, and 2-ethyl-hexyl, or C_6 - C_{24} aryl, such as phenyl, naphthyl, and biphenyl.

10

Preferably, R^{11} , R^{12} and R^{13} are independently of each other H, C_1 - C_{18} alkyl, such as methyl, and ethyl, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D, such as $-CH_2OCH_3$, $-CH_2OCH_2CH_3$, $-CH_2OCH_2CH_2OCH_3$, and $-CH_2OCH_2CH_2OCH_2CH_3$, C_6 - C_{24} aryl, such as phenyl, naphthyl, and biphenyl, C_6 - C_{24} aryl which is substituted by E, such as $-C_6H_4OCH_3$, $-C_6H_4OCH_2CH_3$, $-C_6H_3(OCH_3)_2$, $-C_6H_3(OCH_2CH_3)_2$, $-C_6H_4CH_3$, $-C_6H_3(CH_3)_2$, $-C_6H_2(CH_3)_3$, and $-C_6H_4tBu$, C_2 - C_{18} alkenyl, C_2 - C_{18} alkynyl, C_1 - C_{18} alkoxy, C_1 - C_{18} alkoxy which is substituted by E and/or interrupted by D, such as $-OCH_2OCH_3$, $-OCH_2OCH_2CH_3$, $CH_2OCH_2CH_2OCH_3$, $-OCH_2CH_2OCH_3$, $-OCH_2CH_2OCH_2CH_2OCH_3$ and $-OCH_2CH_2OCH_2CH_2OCH_2CH_3$, methoxy, ethoxy, n-propoxy, iso-propoxy, n-butoxy, isobutoxy, sec-butoxy, hexoxy, octoxy, and 2-ethyl-hexyloxy, and C_7 - C_{25} aralkyl.

15

20


25

D is preferably $-CO-$, $-COO-$, $-S-$, $-SO-$, $-SO_2-$, $-O-$, $-NR^{25}-$, wherein R^{25} is C_1 - C_{18} alkyl, such as methyl, ethyl, n-propyl, iso-propyl, n-butyl, isobutyl, sec-butyl, t-butyl, hexyl, octyl, and 2-ethyl-hexyl, or C_6 - C_{24} aryl, such as phenyl, naphthyl, and biphenyl.

E is preferably $-OR^{29}$, $-SR^{29}$, $-NR^{25}R^{25}$, $-COR^{28}$, $-COOR^{27}$, $-CONR^{25}R^{25}$, or $-CN$, wherein R^{25} , R^{27} , R^{28} and R^{29} are independently of each other C_1 - C_{18} alkyl, such as methyl, ethyl, n-propyl, iso-propyl, n-butyl, isobutyl, sec-butyl, hexyl, octyl, 2-ethyl-hexyl, or C_6 - C_{24} aryl, such as phenyl, naphthyl, and biphenyl.

30

Preferably, at least one of R^1 and R^2 is C_6 - C_{24} aryl or C_2 - C_{20} heteroaryl, which optionally can be substituted. In this case, R^1 and R^2 are preferably selected from



R^6 , R^7 and X^6 are independently of each other H, C_1 - C_{18} alkyl, such as methyl, ethyl, n-propyl, iso-propyl, n-butyl, isobutyl, sec-butyl, t-butyl, hexyl, octyl, 2-ethyl-hexyl, C_1 - C_{18} alkyl

5 which is substituted by E and/or interrupted by D, such as $-CH_2OCH_3$, $-CH_2OCH_2CH_3$, $-CH_2OCH_2CH_2OCH_3$, and $-CH_2OCH_2CH_2OCH_2CH_3$, C_6 - C_{24} aryl, such as phenyl, naphthyl, and biphenyl, C_6 - C_{24} aryl which is substituted by E, such as $-C_6H_4OCH_3$, $-C_6H_4OCH_2CH_3$, $-C_6H_3(OCH_3)_2$, $-C_6H_3(OCH_2CH_3)_2$, $-C_6H_4CH_3$, $-C_6H_3(CH_3)_2$, $-C_6H_2(CH_3)_3$, and $-C_6H_4tBu$,

10 R^8 is H, C_1 - C_{18} alkyl, such as methyl, ethyl, n-propyl, iso-propyl, n-butyl, isobutyl, and sec-butyl, or C_6 - C_{24} aryl, such as phenyl, naphthyl, and biphenyl, and

R^9 and R^{10} are independently of each other H, C_1 - C_{18} alkyl, such as n-butyl, sec-butyl, hexyl, octyl, or 2-ethyl-hexyl, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D, such as






15 $-CH_2(OCH_2CH_2)_wOCH_3$, $w = 1, 2, 3$, or 4 , C_6 - C_{24} aryl, such as phenyl, naphthyl, or biphenyl, C_6 - C_{24} aryl which is substituted by E, such as $-C_6H_4OCH_3$, $-C_6H_4OCH_2CH_3$, $-C_6H_3(OCH_3)_2$, $-C_6H_3(OCH_2CH_3)_2$, $-C_6H_4CH_3$, $-C_6H_3(CH_3)_2$, $-C_6H_2(CH_3)_3$, or $-C_6H_4tBu$, or R^9 and R^{10} together form a 4 to 8 membered ring, especially a 5 or 6 membered ring, such as cyclohexyl, or cyclopentyl.

Most preferred, R^2 is H and R^1 is C_6 - C_{24} aryl or C_2 - C_{20} heteroaryl in formula Ia and Ib.



20 The polymer of the present invention comprise the repeating unit of the formula I in an amount of from 0.5 mol% to 100 mol%, especially in an amount of from 40 mol% to 60 mol%, wherein the sum of all repeating units (monomers) is 100 mol%. Accordingly, the polymers of the present invention can comprise besides the repeating unit of the formula I co-momers in


25 an amount of up to 99.5 mol%, especially in an amount of from 60 mol% to 40 mol%.

Suitable co-monomers T are selected from the group consisting of



5






, wherein

- R^{16} is H; C_6-C_{18} aryl, C_6-C_{18} aryl which is substituted by C_1-C_{18} alkyl, C_1-C_{18} alkyl, C_6-C_{24} aryl, which can optionally be substituted, or C_1-C_{18} alkyl which is interrupted by $-O-$;
- p is an integer from 1 to 10, especially 1, 2 or 3,
- q is an integer from 1 to 10, especially 1, 2 or 3,
- s is an integer from 1 to 10, especially 1, 2 or 3,
- R^6 , R^7 , R^8 , R^9 and R^{10} are as defined above, or
- R^9 and R^{10} together form a group of formula $=CR^{100}R^{101}$, wherein R^{100} and R^{101} are independently of each other H, C_1-C_{18} alkyl, C_1-C_{18} alkyl which is substituted by E and/or interrupted by D, C_6-C_{24} aryl, C_6-C_{24} aryl which is substituted by E, C_2-C_{20} heteroaryl, or C_2-C_{20} heteroaryl which is substituted by E, and
- R^{14} and R^{15} are independently of each other H, C_1-C_{18} alkyl, C_1-C_{18} alkyl which is substituted by E and/or interrupted by D, C_6-C_{24} aryl, C_6-C_{24} aryl which is substituted by E, C_2-C_{20} heteroaryl, or C_2-C_{20} heteroaryl which is substituted by E.


If R^9 and R^{10} together form a group of formula $=CR^{100}R^{101}$, T is preferably a group of formula



, wherein R^{102} and R^{103} are independently of each other C_1-

- C_{18} alkyl, C_1-C_{18} alkoxy, C_6-C_{10} aryl, C_6-C_{10} aryloxy, or $di(C_1-C_{18}alkyl)amino$, wherein the aryl or aryloxy groups optionally can be substituted by C_1-C_8alkyl (cf. US-B-6,512,083).

Preferred examples of T are selected from groups of formula



5 wherein

R^6 and R^7 are independently of each other H, C_1 - C_{18} alkyl, such as methyl, ethyl, n-propyl, iso-propyl, n-butyl, isobutyl, sec-butyl, t-butyl, 2-methylbutyl, n-pentyl, isopentyl, n-hexyl, 2-ethylhexyl, or n-heptyl, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D, such as - CH_2OCH_3 , - $CH_2OCH_2CH_3$, - $CH_2OCH_2CH_2OCH_3$, or - $CH_2OCH_2CH_2OCH_2CH_3$, C_6 - C_{24} aryl, such as phenyl, naphthyl, or biphenyl, C_6 - C_{24} aryl which is substituted by E, such as - $C_6H_4OCH_3$, - $C_6H_4OCH_2CH_3$, - $C_6H_3(OCH_3)_2$, or - $C_6H_3(OCH_2CH_3)_2$, - $C_6H_4CH_3$, - $C_6H_3(CH_3)_2$, - $C_6H_2(CH_3)_3$, or - C_6H_4tBu ,


10 R^8 is H, C_1 - C_{18} alkyl, such as methyl, ethyl, n-propyl, iso-propyl, n-butyl, isobutyl, sec-butyl, t-butyl, 2-methylbutyl, n-pentyl, isopentyl, n-hexyl, 2-ethylhexyl, n-heptyl, or C_6 - C_{24} aryl, such as phenyl, naphthyl, or biphenyl, and

15 R^9 and R^{10} are independently H, C_1 - C_{18} alkyl, such as n-butyl, sec-butyl, hexyl, octyl, or 2-ethyl-hexyl, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D, such as - $CH_2(OCH_2CH_2)_wOCH_3$, $w = 1, 2, 3$, or 4 , C_6 - C_{24} aryl, such as phenyl, naphthyl, or biphenyl, C_6 - C_{24} aryl which is substituted by E, such as - $C_6H_4OCH_3$, - $C_6H_4OCH_2CH_3$, - $C_6H_3(OCH_3)_2$,

20 - $C_6H_3(OCH_2CH_3)_2$, - $C_6H_4CH_3$, - $C_6H_3(CH_3)_2$, - $C_6H_2(CH_3)_3$, or - C_6H_4tBu , or R^9 and R^{10} together form a 4 to 8 membered ring, especially a 5 or 6 membered ring, such as cyclohexyl, or cyclopentyl.

In a preferred embodiment the polymers comprise repeating units of formula Ia or Ib, wherein

25 R^1 is a group of formula



R^2 is H,

R^6 and R^7 are independently of each other H, C_1 - C_{12} alkyl, or C_1 - C_{12} alkoxy,


- 5 R^8 is C_1 - C_{18} alkyl, C_1 - C_{18} alkyl interrupted by one or two oxygen atoms, or C_6 - C_{12} aryl, which optionally can be substituted by C_1 - C_{12} alkyl, or C_1 - C_{12} alkoxy,

R^9 and R^{10} are independently of each other C_1 - C_{18} alkyl, especially C_4 - C_{12} alkyl, which can be interrupted by one or two oxygen atoms, and


X^1 , X^2 , T, x and y are as defined above.

10

In said embodiment a co-monomer T can optionally be present, which is preferably selected from the group consisting of



15




R^9 and R^{10} are independently of each other C_1 - C_{18} alkyl, especially C_4 - C_{12} alkyl, which can be interrupted by one or two oxygen atoms, or

20 R^9 and R^{10} form a five or six membered carbocyclic ring, which optionally can be substituted by C_1 - C_4 alkyl, and

R^8 is C_1 - C_{18} alkyl.

In the first aspect of the present invention polymers are particularly preferred, which comprise a repeating unit of formula



(Ia) and

a co-monomer , wherein
 x is in the range of 0.005 to 1, especially 0.4 to 0.6, and y is in the range of 0.995 to 0, especially 0.6 to 0.4, wherein the sum of x and y is 1,

R^1 is a group of formula , or , or

10 especially , or , or or , wherein X^6 is H, C_1 - C_{18} alkyl, or C_1 - C_{18} alkoxy, R^2 is H,


X^1 and X^2 are independently of each other a group of formula , or

, especially , or , and

15 T is a group of formula , wherein s is one or two, and R^9 and R^{10} are independently of each other C_1 - C_{18} alkyl, especially C_4 - C_{12} alkyl, which can be interrupted by one or two oxygen atoms, and

R^6 and R^7 are independently of each other H, C_1 - C_{12} alkyl, C_6 - C_{24} aryl, especially phenyl, naphthyl, or biphenyl, which can be substituted by $-O$ - C_1 - C_{12} alkyl, or C_1 - C_{18} alkoxy.


5 In a second aspect, the present invention relates to polymers comprising a repeating unit of the formula



(II), wherein


R^3 , R^4 and R^5 are independently of each other an organic substituent, especially C_2 - C_{30} aryl or a C_2 - C_{26} heteroaryl, which optionally can be substituted,

X^3 is a divalent linking group, wherein repeating units of the formula




10

(IIb) are preferred and repeating units of the formula




(IIa), and



(IIc) are especially

preferred.


Examples of suitable divalent linking groups X^3 are




; wherein the dotted line represent the bond to the pyrimidine ring;

R^3 , R^4 and R^5 are as defined above;

- 5 R^{56} and R^{57} are independently of each other H; C_1 - C_{18} alkyl; C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D; C_6 - C_{24} aryl; C_6 - C_{24} aryl which is substituted by E; C_2 - C_{20} heteroaryl; C_2 - C_{20} heteroaryl which is substituted by E; C_2 - C_{18} alkenyl; C_2 - C_{18} alkynyl; C_1 - C_{18} alkoxy; C_1 - C_{18} alkoxy which is substituted by E and/or interrupted by D; or C_7 - C_{25} aralkyl; R^{58} is H; C_1 - C_{18} alkyl; C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D; C_6 - C_{24} aryl; or C_7 - C_{25} aralkyl;
- 10 R^{59} is H; C_1 - C_{18} alkyl; C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D; C_6 - C_{24} aryl; C_6 - C_{24} aryl which is substituted by E; C_2 - C_{20} heteroaryl; C_2 - C_{20} heteroaryl which is substituted by E; C_2 - C_{18} alkenyl; C_2 - C_{18} alkynyl; C_1 - C_{18} alkoxy; C_1 - C_{18} alkoxy which is substituted by E and/or interrupted by D; or C_7 - C_{25} aralkyl;
- 15 D is $-\text{CO}-$; $-\text{COO}-$; $-\text{OCOO}-$; $-\text{S}-$; $-\text{SO}-$; $-\text{SO}_2-$; $-\text{O}-$; $-\text{NR}^{25}-$; $-\text{SiR}^{30}\text{R}^{31}-$; $-\text{POR}^{32}-$; $-\text{CR}^{23}=\text{CR}^{24}-$; or $-\text{C}\equiv\text{C}-$; and
- E is $-\text{OR}^{29}$; $-\text{SR}^{29}$; $-\text{NR}^{25}\text{R}^{26}$; $-\text{COR}^{28}$; $-\text{COOR}^{27}$; $-\text{CONR}^{25}\text{R}^{26}$; $-\text{CN}$; $-\text{OCOOR}^{27}$; or halogen;
- wherein
- R^{23} , R^{24} , R^{25} and R^{26} are independently of each other H; C_6 - C_{18} aryl; C_6 - C_{18} aryl which is substituted by C_1 - C_{18} alkyl; C_1 - C_{18} alkoxy; C_1 - C_{18} alkyl; or C_1 - C_{18} alkyl which is interrupted by $-\text{O}-$; or
- 20 $-\text{O}-$; or



R^{25} and R^{26} together form a five or six membered ring, in particular



R^{27} and R^{28} are independently of each other H; C_6-C_{18} aryl; C_6-C_{18} aryl which is substituted by C_1-C_{18} alkyl, or C_1-C_{18} alkoxy; C_1-C_{18} alkyl; or C_1-C_{18} alkyl which is interrupted by $-O-$, and


- 5 R^{29} is H; C_6-C_{18} aryl; C_6-C_{18} aryl which is substituted by C_1-C_{18} alkyl, C_1-C_{18} alkoxy; C_1-C_{18} alkyl; or C_1-C_{18} alkyl which is interrupted by $-O-$,

R^{71} is H, C_1-C_{18} alkyl, $-C\equiv N$, $-CONR^{25}R^{26}$ or $-COOR^{27}$,

R^{30} and R^{31} are independently of each other C_1-C_{18} alkyl, C_6-C_{18} aryl, or C_6-C_{18} aryl, which is substituted by C_1-C_{18} alkyl, and








- 10 R^{32} is C_1-C_{18} alkyl, C_6-C_{18} aryl, or C_6-C_{18} aryl, which is substituted by C_1-C_{18} alkyl.

In the second aspect of the present invention polymers comprising a repeating unit of formula IIb, especially a repeating unit of formula IIa, or IIc are preferred, wherein X^3 is a




- 15 group of the formula , wherein the dotted line represent the bond to the pyrimidine ring and R^{71} is H, alkyl, $-C\equiv N$, or $-COOR^{27}$, wherein R^{27} is H, or C_1-C_{18} alkyl, which optionally can be interrupted by one or more oxygen atoms, especially C_4-C_{12} alkyl, which can be interrupted by one or two oxygen atoms.

- 20 R^3 , R^4 and R^5 can in principal be any organic substituent, provided it does not have negative influence on the (electro)luminescent characteristics of the polymers, especially H, C_1-C_{18} alkyl, C_1-C_{18} alkyl which is substituted by E and/or interrupted by D, C_2-C_{18} alkenyl, C_2-C_{18} alkynyl, C_1-C_{18} alkoxy, C_1-C_{18} alkoxy which is substituted by E and/or interrupted by D, C_7-C_{25} aralkyl, C_6-C_{24} aryl, or C_2-C_{20} heteroaryl, which optionally can be substituted, especially a group of the formula




wherein m1, m2, m3, m4, m5, m6 and m7 are integers of 1 to 10, in particular 1 to 3,


X^6 is H, C_1 - C_{18} alkyl, C_1 - C_{18} alkoxy, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by




D, C_6 - C_{24} aryl, which can optionally be substituted, especially




or




, C_2 - C_{20} heteroaryl, which can optionally be substituted,



especially



, or



, C_2 - C_{18} alkenyl, C_2 - C_{18} alkynyl, C_1 -

- 5 C_{18} alkoxy, C_1 - C_{18} alkoxy which is substituted by E and/or interrupted by D, or C_7 - C_{25} aralkyl, X^4 is C_1 - C_{18} alkyl, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D, C_6 - C_{24} aryl or C_2 - C_{20} heteroaryl, which can optionally be substituted,

X^5 is C_1 - C_{18} alkyl, C_6 - C_{24} aryl, or C_2 - C_{20} heteroaryl, which can optionally be substituted by $-OC_1$ - C_{18} alkyl or $-OC_6$ - C_{24} aryl,

- 10 R^{61} , R^{62} and R^{63} are independently of each other H, C_1 - C_{18} alkyl, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D, C_6 - C_{24} aryl, C_6 - C_{24} aryl which is substituted by E, C_2 - C_{18} alkenyl, C_2 - C_{18} alkynyl, C_1 - C_{18} alkoxy, C_1 - C_{18} alkoxy which is substituted by E and/or interrupted by D, or C_7 - C_{25} aralkyl,

R^{64} and R^{65} are independently of each other H, C_1 - C_{18} alkyl, C_1 - C_{18} alkyl which is substituted

- 15 by E and/or interrupted by D, C_6 - C_{24} aryl, C_6 - C_{24} aryl which is substituted by E, C_2 - C_{20} heteroaryl, or C_2 - C_{20} heteroaryl which is substituted by E, and
D, E, R^{56} , R^{57} , R^{58} , R^{59} and R^{60} are as defined above.

Preferably, R^{56} and R^{57} are independently of each other H, C_1 - C_{18} alkyl, such as methyl, ethyl,
20 n-propyl, iso-propyl, n-butyl, isobutyl, sec-butyl, t-butyl, 2-methylbutyl, n-pentyl, isopentyl, n-hexyl, 2-ethylhexyl, and n-heptyl, C_1 - C_{18} alkyl, which is substituted by E and/or interrupted by D, such as $-CH_2OCH_3$, $-CH_2OCH_2CH_3$, $-CH_2OCH_2CH_2OCH_3$, and $-CH_2OCH_2CH_2OCH_2CH_3$, C_6 - C_{24} aryl, such as phenyl, naphthyl, and biphenyl, or C_6 - C_{24} aryl, which is substituted by E, such as $-C_6H_4OCH_3$, $-C_6H_4OCH_2CH_3$, $-C_6H_3(OCH_3)_2$, $-C_6H_3(OCH_2CH_3)_2$, $-C_6H_4CH_3$,
25 $-C_6H_3(CH_3)_2$, $-C_6H_2(CH_3)_3$, and $-C_6H_4tBu$.

R^{58} is preferably H, C_1 - C_{18} alkyl, such as methyl, ethyl, n-propyl, iso-propyl, n-butyl, isobutyl, sec-butyl, t-butyl, 2-methylbutyl, n-pentyl, isopentyl, n-hexyl, 2-ethylhexyl, and n-heptyl, or C_6 - C_{24} aryl, such as phenyl, naphthyl, and biphenyl.

- 5 Preferably, R^{59} and R^{60} are independently of each other H, C_1 - C_{18} alkyl, such as n-butyl, sec-butyl, hexyl, octyl, and 2-ethyl-hexyl, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D, such as $-CH_2(OCH_2CH_2)_wOCH_3$, $w=1, 2, 3$, or 4 , C_6 - C_{24} aryl, such as phenyl, naphthyl, and biphenyl, C_6 - C_{24} aryl which is substituted by E, such as $-C_6H_4OCH_3$, $-C_6H_4OCH_2CH_3$, $-C_6H_3(OCH_3)_2$, $-C_6H_3(OCH_2CH_3)_2$, $-C_6H_4CH_3$, $-C_6H_3(CH_3)_2$, $-C_6H_2(CH_3)_3$, and $-C_6H_4tBu$, or R^{59}
 10 and R^{60} together form a 4 to 8 membered ring, preferably a 5 or 6 membered ring, such as cyclohexyl, and cyclopentyl.

- Preferably, R^{64} and R^{65} are independently of each other H, C_1 - C_{18} alkyl, such as methyl, ethyl, n-propyl, iso-propyl, n-butyl, isobutyl, and sec-butyl, or C_6 - C_{24} aryl, such as phenyl, naphthyl,
 15 and biphenyl.

- X^4 is preferably C_1 - C_{18} alkyl, such as methyl, ethyl, n-propyl, iso-propyl, n-butyl, isobutyl, sec-butyl, t-butyl, hexyl, octyl, and 2-ethyl-hexyl, or C_6 - C_{24} aryl, such as phenyl, naphthyl, and biphenyl.
 20


- X^5 is preferably C_1 - C_{18} alkyl, such as methyl, ethyl, n-propyl, iso-propyl, n-butyl, isobutyl, sec-butyl, t-butyl, hexyl, octyl, and 2-ethyl-hexyl, C_6 - C_{24} aryl, such as phenyl, naphthyl, and biphenyl, or C_6 - C_{24} aryl substituted by OR^{29} , wherein R^{29} is H, C_1 - C_{18} alkyl, such as methyl, and ethyl, or C_6 - C_{24} aryl, such as phenyl.
 25

- D is preferably $-CO-$; $-COO-$; $-OCOO-$; $-S-$; $-SO-$; $-SO_2-$; $-O-$; $-NR^{25}-$; and E is preferably $-OR^{29}$; $-SR^{29}$; $-NR^{25}R^{26}$; $-COR^{28}$; $-COOR^{27}$; $-CONR^{25}R^{26}$; or $-CN$; wherein R^{25} ; R^{27} ; R^{28} and R^{29} are independently of each other H; C_1 - C_{18} alkyl; such as methyl; ethyl; n-propyl; iso-propyl; n-butyl; isobutyl; sec-butyl; hexyl; octyl; and 2-ethyl-hexyl; C_6 - C_{24} aryl; such as phenyl;
 30 naphthyl, and biphenyl.

- Preferably, at least one of R^1 , R^2 and R^3 is C_6 - C_{24} aryl or C_2 - C_{20} heteroaryl, which optionally can be substituted. In this aspect, polymers comprising repeating units of formula IIa, wherein R^4 is H and R^3 and R^5 are independently of each other C_6 - C_{24} aryl, or C_2 -
 35 C_{20} heteroaryl, or IIc, wherein R^3 is H and R^4 and R^5 are independently of each other C_6 - C_{24} aryl or C_2 - C_{20} heteroaryl, are preferred against those polymers having repeating units of

formula IIb, wherein R^3 , R^4 , and R^5 are independently of each other C_6 - C_{24} aryl or C_2 - C_{20} heteroaryl, wherein the C_6 - C_{24} aryl or C_2 - C_{20} heteroaryl can optionally be substituted.

Preferably, R^3 , R^4 , and R^5 are independently of each other H,



5 , , , or , wherein R^{59} and R^{60} are independently of each other C_1 - C_{18} alkyl, especially C_4 - C_{12} alkyl, which can be interrupted by one or two oxygen atoms, wherein polymers comprising repeating units of




formula IIb, wherein R^3 , R^4 , and R^5 are independently of each other




, , , or , and polymers

10 comprising repeating units of formula (IIa), wherein R^4 is H and R^3 and R^5 are independently

of each other







or




, and polymers comprising repeating units of formula (IIc), wherein R^3 is H

and R^4 and R^5 are independently of each other



, or




, are especially preferred.

5

Suitable co-monomers T are selected from the group consisting of





wherein p is an integer from 1 to 10, especially 1, 2 or 3,

5 q is an integer from 1 to 10, especially 1, 2 or 3,

s is an integer from 1 to 10, especially 1, 2 or 3,

p is an integer from 1 to 10, especially 1, 2 or 3,

R^{72} is H; C_6-C_{18} aryl; C_6-C_{18} aryl, which is substituted by C_1-C_{18} alkyl, C_1-C_{18} alkoxy; C_1-C_{18} alkyl; or C_1-C_{18} alkyl, which is interrupted by $-O-$;

10 R^{56} , R^{57} , R^{58} , R^{59} , R^{60} , R^{64} and R^{65} are as defined above, or

R^{59} and R^{60} together form a group of formula $=CR^{100}R^{101}$, wherein

R^{100} and R^{101} are independently of each other H, C_1-C_{18} alkyl, C_1-C_{18} alkyl which is substituted by E and/or interrupted by D, C_6-C_{24} aryl, C_6-C_{24} aryl which is substituted by E, or C_2-C_{20} heteroaryl, or C_2-C_{20} heteroaryl which is substituted by E.

15


Preferably, R^{56} and R^{57} are independently of each other H, C_1-C_{18} alkyl, such as methyl, ethyl, n-propyl, iso-propyl, n-butyl, isobutyl, sec-butyl, t-butyl, 2-methylbutyl, n-pentyl, isopentyl, n-hexyl, 2-ethylhexyl, and n-heptyl, C_1-C_{18} alkyl, which is substituted by E and/or interrupted by D, such as $-CH_2OCH_3$, $-CH_2OCH_2CH_3$, $-CH_2OCH_2CH_2OCH_3$, and $-CH_2OCH_2CH_2OCH_2CH_3$, C_6-C_{24} aryl, such as phenyl, naphthyl, and biphenyl, or C_6-C_{24} aryl, which is substituted by E, such as $-C_6H_4OCH_3$, $-C_6H_4OCH_2CH_3$, $-C_6H_3(OCH_3)_2$, $-C_6H_3(OCH_2CH_3)_2$, $-C_6H_4CH_3$, $-C_6H_3(CH_3)_2$, $-C_6H_2(CH_3)_3$, and $-C_6H_4tBu$.

20

R^{58} is preferably H, C_1-C_{18} alkyl, such as methyl, ethyl, n-propyl, iso-propyl, n-butyl, isobutyl, sec-butyl, t-butyl, 2-methylbutyl, n-pentyl, isopentyl, n-hexyl, 2-ethylhexyl, and n-heptyl, or C_6-C_{24} aryl, such as phenyl, naphthyl, and biphenyl.

25

If R^{59} and R^{60} together form a group of formula $=CR^{100}R^{101}$, T is preferably a group of formula




, wherein R^{102} and R^{103} are independently of each other C_1 -

C_{18} alkyl, C_1 - C_{18} alkoxy, C_6 - C_{10} aryl, C_6 - C_{10} aryloxy, or di(C_1 - C_{18} alkyl)amino, wherein the aryl or aryloxy groups optionally can be substituted by C_1 - C_8 alkyl (cf. US-B-6,512,083).



10 Preferably, R^{59} and R^{60} are independently of each other H, C_1 - C_{18} alkyl, such as n-butyl, sec-butyl, hexyl, octyl, and 2-ethyl-hexyl, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D, such as $-CH_2(OCH_2CH_2)_wOCH_3$, $w=1, 2, 3$, or 4, C_6 - C_{24} aryl, such as phenyl, naphthyl, and biphenyl, C_6 - C_{24} aryl which is substituted by E, such as $-C_6H_4OCH_3$, $-C_6H_4OCH_2CH_3$, $-C_6H_3(OCH_3)_2$, $-C_6H_3(OCH_2CH_3)_2$, $-C_6H_4CH_3$, $-C_6H_3(CH_3)_2$, $-C_6H_2(CH_3)_3$, and $-C_6H_4tBu$, or R^{59} and R^{60} together form a 4 to 8 membered ring, preferably a 5 or 6 membered ring, such as cyclohexyl, and cyclopentyl.

15 Preferably, R^{64} and R^{65} are independently of each other H, C_1 - C_{18} alkyl, such as methyl, ethyl, n-propyl, iso-propyl, n-butyl, isobutyl, and sec-butyl, or C_6 - C_{24} aryl, such as phenyl, naphthyl, and biphenyl.

A preferred embodiment is directed to polymers comprising a repeating unit of formula IIb,



20 especially a repeating unit of formula IIa, or IIc, and a co-monomer, wherein x is in the range of 0.005 to 1, especially 0.4 to 0.6, and y is in the range of 0.995 to 0, especially 0.6 to 0.4, wherein the sum of x and y is 1, wherein




X^3 is a group of the formula

, or


, wherein the dotted line

represent the bond to the pyrimidine ring,

25 R^3 , R^4 and R^5 are independently of each other a group of the formula



T is a group of formula



5


R^{56} , R^{57} and X^6 are independently of each other C_1 - C_{18} alkyl, C_1 - C_{18} alkyl, which is substituted by E and/or interrupted by D, C_6 - C_{24} aryl, C_6 - C_{24} aryl, which is substituted by E, R^{59} and R^{60} are independently of each other C_1 - C_{18} alkyl, C_1 - C_{18} alkyl, which is substituted by $-OR^{29}$ and/or interrupted by $-O-$,

10


R^{71} is H, $-CONR^{25}R^{25}$ or $-CN$, wherein D is $-O-$, or $-NR^{25}-$, E is $-OR^{29}$, $-SR^{29}$, or $-NR^{25}R^{25}$, wherein R^{25} is H, C_1 - C_{18} alkyl, or C_6 - C_{24} aryl, and R^{29} is C_1 - C_{18} alkyl, C_6 - C_{24} aryl.

15

A particularly preferred embodiment is directed to polymers, comprising a repeating unit of



formula IIb, especially a repeating unit of formula IIa, or IIc, and a co-monomer, wherein x is in the range of 0.005 to 1, especially 0.4 to 0.6, and y is in the range of 0.995 to 0, especially 0.6 to 0.4, wherein the sum of x and y is 1,




20

X^3 is a group of the formula, wherein the dotted line represent the bond to the pyrimidine ring and R^{71} is H, alkyl, $-C\equiv N$, or $-COOR^{27}$, wherein R^{27} is H, or C_1 - C_{18} alkyl, which


optionally can be interrupted by one or more oxygen atoms, especially C₄-C₁₂alkyl, which can be interrupted by one or two oxygen atoms,

R³, R⁴ and R⁵ are independently of each other H,



5 T is a group of formula


wherein R⁵⁹ and R⁶⁰ are independently of each other C₁-C₁₈alkyl, especially C₄-C₁₂alkyl, which can be interrupted by one or two oxygen atoms, are preferred; and polymers




comprising repeating units of formula

(IIb), wherein R³, R⁴, and

R⁵ are independently of each other




10





(IIa), wherein R⁴ is H and R³ and R⁵ are independently


formula







of each other



or , and polymers comprising repeating units of formula




(IIc), wherein R^3 is H and R^4 and R^5 are independently of each

other , , , , or



, wherein X^3 is a group of the formula , wherein the dotted line

- 5 represent the bond to the pyrimidine ring and R^{71} is H, alkyl, $-C\equiv N$, or $-COOR^{27}$, wherein R^{27} is H; or C_1 - C_{18} alkyl; which optionally can be interrupted by one or more oxygen atoms, especially C_4 - C_{12} alkyl, which can be interrupted by one or two oxygen atoms, and



T is a group of formula





wherein R^{59} and R^{60} are independently of each other C_1 - C_{18} alkyl, especially C_4 - C_{12} alkyl, which can be interrupted by one or two oxygen atoms, are especially preferred.

10

The polymers of this invention preferably have a weight average molecular weight of 50,000 Daltons or greater, more preferably 100,000 Daltons or greater, and most preferably 150,000 Daltons or greater; preferably 1,000,000 Daltons or less, more preferably 500,000 Daltons or less and most preferably 250,000 Daltons or less. Molecular weights are determined

15

A further embodiment of the present invention is represented by the monomers of the formula




- 5 R^1, R^2, R^3, R^4 and R^5 are independently of each other an organic substituent, especially a C_2 - C_{30} aryl or a C_2 - C_{26} heteroaryl, which optionally can be substituted, X^1, X^2 , and X^3 are independently of each other a divalent linking group, and

- 10 X^{11} is independently in each occurrence a halogen atom, or $-B(OH)_2$, $-B(OY^1)_2$ or $-B(OY^1)(OY^2)$, wherein Y^1 is independently in each occurrence a C_1 - C_{10} alkyl group and Y^2 is independently in each occurrence a C_2 - C_{10} alkylene group, such as $-CY^3Y^4-CY^5Y^6-$, or $-CY^7Y^8-CY^9Y^{10}-$, $-CY^{11}Y^{12}-$, wherein $Y^3, Y^4, Y^5, Y^6, Y^7, Y^8, Y^9, Y^{10}, Y^{11}$ and Y^{12} are independently of each other hydrogens, or a C_1 - C_{10} alkyl group, especially $-C(CH_3)_2C(CH_3)_2-$, or $-C(CH_3)_2CH_2C(CH_3)_2-$, which are starting materials in the preparation of the polymers of formula I and II.

- 15 The pyrimidine starting compounds are known or can be prepared according to or analogous to known procedures. The present pyrimidine compounds are for instance derivatives of known hydroxyphenyl pyrimidine compounds: US-A-3,442,898, US-A-5,597,854 and US-A-5,753,729, the relevant parts of which are hereby incorporated by reference. The present

pyrimidine compounds can for instance be prepared according to or analogous to the following procedure:



are as defined above and X^{11} is a halogen atom.

- 5 An amidine hydrochloride is added to a 2-propen-1-one derivative in a C_1 - C_4 -alcohol, like methanol, ethanol, propanol or butanol. A base, for example, an alkali metal hydroxide or alkoxide, such as sodium methoxide or potassium hydroxide is added and the solution is stirred in the presence of oxygen, for example dry air (see, for example European patent application no. 03405047.6; example 8).

10

The boron-containing compounds of formula (IV) may be prepared by any suitable method. An example of reaction conditions for preparing boron-containing compounds is described in Remmers et al., *Macromolecular Rapid Communications*, Vol. 17, 239-253 (1996).

- 15 Compounds of formulas (IV), which are disubstituted by chlorine or bromine, are converted to the corresponding dilithio derivative by reaction with two equivalents of butyllithium. Reaction of the dilithio derivative with a trialkylborate followed by hydrolysis yields the diboronic acid derivative. Esterification of the diboronic acid derivative with an alkylene diol, such as ethylene glycol, gives the di(cyclic)boronate derivative.

- 20 Halogen is fluorine, chlorine, bromine and iodine.

C_1 - C_{18} alkyl is a branched or unbranched radical such as for example methyl, ethyl, propyl, isopropyl, n-butyl, sec-butyl, isobutyl, tert-butyl, 2-ethylbutyl, n-pentyl, isopentyl, 1-methylpentyl, 1,3-dimethylbutyl, n-hexyl, 1-methylhexyl, n-heptyl, isoheptyl, 1,1,3,3-tetramethylbutyl, 1-methylheptyl, 3-methylheptyl, n-octyl, 2-ethylhexyl, 1,1,3-trimethylhexyl, 1,1,3,3-tetramethylpentyl, nonyl, decyl, undecyl, 1-methylundecyl, dodecyl, 1,1,3,3,5,5-hexamethylhexyl, tridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, or octadecyl.

25

C_1 - C_{18} alkoxy radicals are straight-chain or branched alkoxy radicals, e.g. methoxy, ethoxy, n-propoxy, isopropoxy, n-butoxy, sec-butoxy, tert-butoxy, amyloxy, isoamyloxy or tert-amyloxy, heptyloxy, octyloxy, isooctyloxy, nonyloxy, decyloxy, undecyloxy, dodecyloxy, tetradecyloxy, pentadecyloxy, hexadecyloxy, heptadecyloxy and octadecyloxy.

30

C_2 - C_{18} alkenyl radicals are straight-chain or branched alkenyl radicals, such as e.g. vinyl, allyl, methallyl, isopropenyl, 2-butenyl, 3-butenyl, isobutenyl, n-penta-2,4-dienyl, 3-methyl-but-2-enyl, n-oct-2-enyl, n-dodec-2-enyl, isododecenyl, n-dodec-2-enyl or n-octadec-4-enyl.

- 5 C_{2-24} alkynyl is straight-chain or branched and preferably C_{2-8} alkynyl, which may be unsubstituted or substituted, such as, for example, ethynyl, 1-propyn-3-yl, 1-butyne-4-yl, 1-pentyne-5-yl, 2-methyl-3-butyne-2-yl, 1,4-pentadiyne-3-yl, 1,3-pentadiyne-5-yl, 1-hexyne-6-yl, cis-3-methyl-2-penten-4-yn-1-yl, trans-3-methyl-2-penten-4-yn-1-yl, 1,3-hexadiyne-5-yl, 1-octyne-8-yl, 1-nonyne-9-yl, 1-decyn-10-yl, or 1-tetracosyn-24-yl.

- 10 C_4 - C_{18} cycloalkyl is preferably C_5 - C_{12} cycloalkyl, such as, for example, cyclopentyl, cyclohexyl, cycloheptyl, cyclooctyl, cyclononyl, cyclodecyl, cyclododecyl. Cyclohexyl and cyclopentyl are most preferred.



- 15 C_2 - C_{18} alkenyl is for example vinyl, allyl, butenyl, pentenyl, hexenyl, heptenyl, or octenyl.

Aryl is usually C_6 - C_{30} aryl, preferably C_6 - C_{24} aryl, which optionally can be substituted, such as, for example, phenyl, 4-methylphenyl, 4-methoxyphenyl, naphthyl, biphenyl, 2-fluorenyl, phenanthryl, anthryl, tetracyl, pentacyl, hexacyl, terphenyl or quadphenyl.

- 20 C_7 - C_{24} aralkyl radicals are preferably C_7 - C_{15} aralkyl radicals, which may be substituted, such as, for example, benzyl, 2-benzyl-2-propyl, β -phenethyl, α,α -dimethylbenzyl, ω -phenyl-butyl, ω -phenyl-octyl, ω -phenyl-dodecyl or 3-methyl-5-(1',1',3',3'-tetramethyl-butyl)-benzyl.

- 25 C_6 - C_{30} heteroaryl is a ring with five to seven ring atoms or a condensed ring system, wherein nitrogen, oxygen or sulfur are the possible hetero atoms, and is typically an unsaturated heterocyclic radical with five to 30 atoms having at least six conjugated π -electrons such as thienyl, benzo[b]thienyl, dibenzo[b,d]thienyl, thianthrenyl, furyl, furfuryl, 2H-pyranyl, benzofuranyl, isobenzofuranyl, dibenzofuranyl, phenoxythienyl, pyrrolyl, imidazolyl, pyrazolyl, pyridyl, bipyridyl, triazinyl, pyrimidinyl, pyrazinyl, pyridazinyl, indolizynyl, isoindolyl, indolyl, indazolyl, purinyl, quinolizynyl, chinolyl, isochinolyl, phthalazinyl, naphthyridinyl, chinoxalynyl, chinazolynyl, cinnolynyl, pteridinyl, carbazolyl, carbolynyl, benzotriazolyl, benzoxazolyl, phenanthridinyl, acridinyl, perimidinyl, phenanthrolinyl, phenazinyl, isothiazolyl, phenothiazinyl, isoxazolyl, furazanyl or phenoxazinyl, which can be unsubstituted or
- 35 substituted.

Examples of a five or six membered ring formed by R^6 and R^7 and R^{56} and R^{57} , respectively are heterocycloalkanes or heterocycloalkenes having from 3 to 5 carbon atoms which can have one additional hetero atom selected from nitrogen, oxygen and sulfur, for example



Possible substituents of the above-mentioned groups are C_1 - C_8 alkyl, a hydroxyl group, a mercapto group, C_1 - C_8 alkoxy, C_1 - C_8 alkylthio, halogen, halo- C_1 - C_8 alkyl, a cyano group, an aldehyde group, a ketone group, a carboxyl group, an ester group, a carbamoyl group, an amino group, a nitro group or a silyl group.

The term "haloalkyl" means groups given by partially or wholly substituting the above-mentioned alkyl group with halogen, such as trifluoromethyl etc. The "aldehyde group, ketone group, ester group, carbamoyl group and amino group" include those substituted by an alkyl group, a cycloalkyl group, an aryl group, an aralkyl group or a heterocyclic group, wherein the alkyl group, the cycloalkyl group, the aryl group, the aralkyl group and the heterocyclic group may be unsubstituted or substituted. The term "silyl group" means a group of formula $-SiR^{105}R^{106}R^{107}$, wherein R^{105} , R^{106} and R^{107} are independently of each other a C_1 - C_8 alkyl group, in particular a C_1 - C_4 alkyl group, a C_6 - C_{24} aryl group or a C_7 - C_{12} aralkylgroup, such as a trimethylsilyl group.

If a substituent, such as, for example R^6 , R^7 , R^{56} and R^{57} , occurs more than one time in a group, it can be different in each occurrence.

As described above, the aforementioned radicals may be substituted by E and/or, if desired, interrupted by D. Interruptions are of course possible only in the case of radicals containing at least 2 carbon atoms connected to one another by single bonds; C_6 - C_{18} aryl is not interrupted; interrupted arylalkyl or alkylaryl contains the unit D in the alkyl moiety. C_1 - C_{18} alkyl substituted by one or more E and/or interrupted by one or more units D is, for


example, $(\text{CH}_2\text{CH}_2\text{O})_n\text{-R}^x$, where n is a number from the range 1-9 and R^x is H or $\text{C}_1\text{-C}_{10}$ alkyl or $\text{C}_2\text{-C}_{10}$ alkanoyl (e.g. $\text{CO-CH}(\text{C}_2\text{H}_5)\text{C}_4\text{H}_9$), $\text{CH}_2\text{-CH}(\text{OR}^y)\text{-CH}_2\text{-O-R}^y$, where R^y is $\text{C}_1\text{-C}_{18}$ alkyl, $\text{C}_5\text{-C}_{12}$ cycloalkyl, phenyl, $\text{C}_7\text{-C}_{15}$ phenylalkyl, and R^y embraces the same definitions as R^x or is H;

- 5 $\text{C}_1\text{-C}_8$ alkylene-COO- R^z , e.g. CH_2COOR^z , $\text{CH}(\text{CH}_3)\text{COOR}^z$, $\text{C}(\text{CH}_3)_2\text{COOR}^z$, where R^z is H, $\text{C}_1\text{-C}_{18}$ alkyl, $(\text{CH}_2\text{CH}_2\text{O})_{1-9}\text{-R}^x$, and R^x embraces the definitions indicated above;
 $\text{CH}_2\text{CH}_2\text{-O-CO-CH=CH}_2$; $\text{CH}_2\text{CH}(\text{OH})\text{CH}_2\text{-O-CO-C}(\text{CH}_3)=\text{CH}_2$.

10 The polymers containing groups of formulas (I) and (II) may be prepared by any suitable process, but are preferably prepared by the processes described below. The condensation reaction of an aromatic boronate and a bromide, commonly referred to as the "Suzuki reaction", is tolerant of the presence of a variety of organic functional groups and as reported by N. Miyaura and A. Suzuki in Chemical Reviews, Vol. 95, pp. 457-2483 (1995). This reaction can be applied to preparing high molecular weight polymers and copolymers.

15

To prepare polymers corresponding to formula I or II, a dibromide corresponding to formula III, or IV, or a mixture thereof is reacted with an equimolar amount of diboronic acid or diboronate corresponding to formula III, or IV, or a mixture thereof, preferably co-monomer



, wherein X^{11} is independently in each occurrence a halogen atom, or

- 20 ---B(OH)_2 , $\text{---B(OY}^1)_2$ or $\text{---B}\begin{array}{c} \text{O} \\ \diagup \quad \diagdown \\ \text{O} \quad \text{Y}^2 \end{array}$, wherein Y^1 is independently in each occurrence a $\text{C}_1\text{-C}_{10}$ alkyl group and Y^2 is independently in each occurrence a $\text{C}_2\text{-C}_{10}$ alkylene group, such as $\text{---CY}^3\text{Y}^4\text{---CY}^5\text{Y}^6\text{---}$, or $\text{---CY}^7\text{Y}^8\text{---CY}^9\text{Y}^{10}\text{---CY}^{11}\text{Y}^{12}\text{---}$, wherein Y^3 , Y^4 , Y^5 , Y^6 , Y^7 , Y^8 , Y^9 , Y^{10} , Y^{11} and Y^{12} are independently of each other hydrogen, or a $\text{C}_1\text{-C}_{10}$ alkyl group, especially $\text{---C}(\text{CH}_3)_2\text{C}(\text{CH}_3)_2\text{---}$, or $\text{---C}(\text{CH}_3)_2\text{CH}_2\text{C}(\text{CH}_3)_2\text{---}$, under the catalytic action of Pd and

- 25 triphenylphosphine. The reaction is typically conducted at about 70 °C to 120 °C in an aromatic hydrocarbon solvent such as toluene. Other solvents such as dimethylformamide and tetrahydrofuran can also be used alone, or in mixtures with an aromatic hydrocarbon. An aqueous base, preferably sodium carbonate or bicarbonate, is used as the HBr scavenger. Depending on the reactivities of the reactants, a polymerization reaction may take 2 to 100
 30 hours. Organic bases, such as, for example, tetraalkylammonium hydroxide, and phase transfer catalysts, such as, for example TBAB, can promote the activity of the boron (see, for example, Leadbeater & Marco; Angew. Chem. Int. Ed., 2003, 42, 1407 and references cited therein). Other variations of reaction conditions are given by T. I. Wallow and B. M. Novak in

Journal of Organic Chemistry, Vol. 59, pp. 5034-5037 (1994); and M. Remmers, M. Schulze, and G. Wegner in Macromolecular Rapid Communications, Vol. 17, pp. 239-252 (1996).

An alternating copolymer results when a dibromide corresponding to formula (III) or (IV) is

5 reacted with a diboronate corresponding to formula
$$X^{11}-\left[T-\right]_y X^{11}$$
, wherein X^{11} is

independently in each occurrence $-B(OH)_2$, $-B(OY^1)_2$ or
$$-B \begin{array}{c} \diagup O \diagdown \\ \diagdown O \diagup \end{array} Y^2$$
, wherein Y^1 is independently in each occurrence a C_1 - C_{10} alkyl group and Y^2 is independently in each occurrence a C_2 - C_{10} alkylene group, such as $-CY^3Y^4-CY^5Y^6-$, or $-CY^7Y^8-CY^9Y^{10}-CY^{11}Y^{12}-$, wherein Y^3 , Y^4 , Y^5 , Y^6 , Y^7 , Y^8 , Y^9 , Y^{10} , Y^{11} and Y^{12} are independently of each other hydrogen, 10 or a C_1 - C_{10} alkyl group, especially $-C(CH_3)_2C(CH_3)_2-$, or $-C(CH_3)_2CH_2C(CH_3)_2-$. If desired, a monofunctional aryl halide or aryl boronate may be used as a chain-terminator in such reactions, which will result in the formation of a terminal aryl group.

Polymerization processes involving only dihalo-functional reactants may be carried out using 15 nickel coupling reactions. One such coupling reaction was described by Colon et al. in Journal of Polymer Science, Part A, Polymer Chemistry Edition, Vol. 28, p. 367 (1990), and by Colon et al. in Journal of Organic Chemistry, Vol. 51, p. 2627 (1986). The reaction is typically conducted in a polar aprotic solvent (e.g., dimethylacetamide) with a catalytic amount of nickel salt, a substantial amount of triphenylphosphine and a large excess of zinc. 20 dust. A variant of this process is described by Ioyda et al. in Bulletin of the Chemical Society of Japan, Vol. 63, p. 80 (1990) wherein an organo-soluble iodide was used as an accelerator. Another nickel-coupling reaction was disclosed by Yamamoto in Progress in Polymer Science, Vol. 17, p. 1153 (1992) wherein a mixture of dihaloaromatic compounds were treated with an excess amount of nickel (1,5-cyclooctadiene) complex in an inert solvent. All 25 nickel-coupling reactions when applied to reactant mixtures of two or more aromatic dihalides yield essentially random copolymers. Such polymerization reactions may be terminated by the addition of small amounts of water to the polymerization reaction mixture, which will replace the terminal halogen groups with hydrogen groups. Alternatively, a monofunctional aryl halide may be used as a chain-terminator in such reactions, which will result in the 30 formation of a terminal aryl group.

In one embodiment, the polymers of the invention contain conjugated groups other than the pyrimidine groups described above. "Conjugated groups" refer to moieties containing double bonds, triple bonds and/or aromatic rings. Examples of such groups are the above

mentioned co-monomers T. The incorporation of such groups into the polymer may be used to modify the light absorption, ionization potential, and/or electronic properties of the polymer. Such polymers may be prepared using the methods described above incorporating at least one conjugated compound different from the pyrimidine compounds described above. Such

5 conjugated compounds, hereinafter referred to as "comonomers", have functional groups which permit them to copolymerize with the pyrimidine compounds. For example, dihalo-functional comonomers are preferably used in conjunction with dihalo-functional pyrimidine compounds in nickel-coupling polymerization reactions; dihalo-functional comonomers are preferably used in conjunction with pyrimidine-diboronic acids or pyrimidine-diboronates; and

10 conjugated comonomers bearing diboronic acid or diboronate functionalities are preferably used in conjunction with dihalopyrimidines. For the purpose of preparing polymers of the invention, more than one diboronic acid/diboronate and more than one dibromide may be used in a Suzuki polymerization reaction so long as the total molar amount of diboronic acids/diboronates is essentially equivalent to the total amount of dibromides.

15 Nickel-coupling polymerizations yield essentially random copolymers comprising pyrimidine group-containing units and units derived from other co-monomers, while Suzuki polymerizations yield alternating copolymers.

20 It is possible to control the sequencing of the monomeric units in the resulting copolymer by controlling the order and composition of monomer feeds in the Suzuki reaction. For instance, a high molecular weight copolymer comprising mainly large blocks of pyrimidine homopolymers connected to short blocks of alternating pyrimidine co-monomer oligomers may be made by first introducing into the reaction reactants in the appropriate ratio to make


25 the alternating pyrimidine-comonomer oligomers followed by the remainder of pyrimidine monomers so long as there is an overall balance of boronic and bromo groups.

Usually the polymers of the present invention comprise end moieties E^1 , wherein E^1 is hydrogen or an aryl moiety which may optionally be substituted with a reactive group capable

30 of ~~undergoing~~ chain extension or crosslinking, or a tri(C_1 - C_{18})alkylsiloxy group. As used herein, a reactive group capable of undergoing chain extension or crosslinking refers to any group which is capable of reacting with another of the same group or another group so as to form a link to prepare oligomers or polymers. Preferably, such reactive group is a hydroxy, glycidyl ether, acrylate ester, methacrylate ester, ethenyl, ethynyl, maleimide, nadimide,

35 trifluorovinyl ether moiety or a cyclobutene moiety fused to the aromatic ring of E^1 .

The polymers of the present invention, where E^1 are reactive groups as defined above, are capable of crosslinking to form solvent resistant, heat-resistant films at 100°C or more, more preferably at 150°C or more. Preferably, such crosslinking occurs at 350°C or less, more preferably 300°C or less and most preferably 250°C or less. The crosslinkable polymers of the invention are stable at 100°C or more and more preferably 150°C or more. "Stable" as used herein means that such polymers do not undergo crosslinking or polymerization reactions at or below the stated temperatures. If a crosslinkable material is desired, E^1 is preferably a vinylphenyl, an ethynylphenyl, or 4-(or 3-)benzocyclobutenyl radical. In another embodiment, E is selected from a group of phenolic derivatives of the formula $-C_6H_4-O-Y$, wherein Y is



The end-capping agent E^1-X (E^1 is as defined above and X is either Cl or Br) is incorporated into the polymers of the present invention under the condition in which the resulting polymers are substantially capped by the reactive group E^1 . The reactions useful for this purpose are the nickel-coupling and Suzuki reactions described above. The average degree of polymerization is controlled by the mole ratio of monomers to end-capping agent.

Depending on the process of preparation the polymers of the present invention can be block copolymers, random copolymers, or alternating copolymers.

Another aspect of this invention is related to polymer blends containing 1 to 99 percent of at least one pyrimidine containing polymers of this invention. The remainder 1 percent to 99 percent of the blend is composed of one or more polymeric materials selected from among chain growth polymers such as polystyrene, polybutadiene, poly(methyl methacrylate), and poly(ethylene oxide); step-growth polymers such as phenoxy resins, polycarbonates, polyamides, polyesters, polyurethanes, and polyimides; and crosslinked polymers such as crosslinked epoxy resins, crosslinked phenolic resins, crosslinked acrylate resins, and crosslinked urethane resins. Examples of these polymers may be found in Preparative Methods of Polymer Chemistry, W. R. Sorenson and T. W. Campbell, Second Edition, Interscience Publishers (1968). Also may be used in the blends are conjugated polymers such as poly(phenylene vinylene), substituted poly(phenylene vinylene)s, substituted

polyphenylenes and polythiophenes. Examples of these conjugated polymers are given by Greenham and Friend in Solid State Physics, Vol. 49, pp. 1-149 (1995).

Another aspect of the invention is the films formed from the polymers of the invention. Such
5 films can be used in polymeric light-emitting diodes. Preferably, such films are used as
emitting layers. These polymers may also be used as protective coatings for electronic
devices and as fluorescent coatings. The thickness of the coating or film is dependent upon
the ultimate use. Generally, such thickness can be from 0.01 to 200 microns. In that
10 embodiment wherein the coating is used as a fluorescent coating, the coating or film
thickness is from 50 to 200 microns. In that embodiment where the coatings are used as
electronic protective layers, the thickness of the coating can be from 5 to 20 microns. In that
embodiment where the coatings are used in a polymeric light-emitting diode, the thickness of
the layer formed is 0.05 to 2 microns. The polymers of the invention form good pinhole- and
15 defect-free films. Such films can be prepared by means well known in the art including spin-
coating, spray-coating, dip-coating and roller-coating. Such coatings are prepared by a
process comprising applying a composition to a substrate and exposing the applied
composition to conditions such that a film is formed. The conditions which form a film depend
upon the application technique and the reactive end groups of the aryl moiety. In a preferred
20 embodiment, the composition applied to the substrate comprises the pyrimidine polymers
dissolved in a common organic solvent. Preferably, the solution contains from 0.1 to 10
weight percent of the polymers. This composition is applied to the appropriate substrate by
the desired method and the solvent is allowed to evaporate. Residual solvent may be
removed by vacuum and/or by heat. After removal of the solvent, the coating is then exposed
25 to the necessary conditions to cure the film, if needed, to prepare a film having high solvent
and heat resistance. The films are preferably substantially uniform in thickness and
substantially free of pinholes. In another embodiment, the polymers may be partially cured.
This is known as B-staging.

A further embodiment of the present invention is directed to an optical device or a component
30 therefore, comprising a substrate and a polymer according to the present invention.

A device according to the present invention may be prepared in accordance with the
disclosure of WO99/48160, the contents of which are incorporated by reference. Polymers
according to the present invention may be present in the device as the sole light emitting
35 polymer or as a component in a blend further comprising hole and/or electron transporting

polymers. Alternatively, the device may comprise distinct layers of a polymer of the present invention, a hole transporting polymer and/or an electron transporting polymer.

In one embodiment the optical device comprises an electroluminescent device, which
5 comprises

- (a) a charge injecting layer for injecting positive charge carriers,
- (b) a charge injecting layer for injecting negative charge carriers,
- (c) a light-emissive layer located between the layers (a) and (b) comprising a polymer according to the present invention.

10 The layer (a) may be a positive charge carrier transport layer which is located between the light emissive layer (c) and an anode electrode layer, or may be an anode electrode layer.

The layer (b) may be a negative charge carrier transport layer which is located between the light emissive layer (c) and an cathode electrode layer, or may be an cathode electrode

15 layer. Optionally, an organic charge transport layer can be located between the light emissive layer (c) and one of the charge carrier injecting layers (a) and (b).

The EL device emits light below 520 nm, especially between 380 nm and 520 nm.

20 The EL device has a NTSC coordinate of between about (0.12, 0.05) and about (0.16, 0.10), especially a NTSC coordinate of about (0.14, 0.08).

It will be appreciated that the light emissive layer may be formed from a blend or mixture of materials including one or more polymers according to the present invention, and optionally
25 further different polymers. The further different polymers may be so-called hole transport polymers (i.e. to improve the efficiency of hole transport to the light-emissive material) or electron-transport polymers (i.e. to improve the efficiency of electron transport to the light-emissive material). Preferably, the blend or mixture would comprise at least 0.1 % by weight of a polymer according to the present invention, preferably from 0.2 to 50%, more preferably
30 from 0.5 to 30% by weight.

An organic EL device typically consists of an organic film sandwiched between an anode and a cathode such that when a positive bias is applied to the device, holes are injected into the organic film from the anode, and electrons are injected into the organic film from the cathode.

35 The combination of a hole and an electron may give rise to an exciton, which may undergo radiative decay to the ground state by liberating a photon. In practice the anode is commonly

an mixed oxide of tin and indium for its conductivity and transparency. The mixed oxide (ITO) is deposited on a transparent substrate such as glass or plastic so that the light emitted by the organic film may be observed. The organic film may be the composite of several individual layers each designed for a distinct function. Since holes are injected from the anode, the layer next to the anode needs to have the functionality of transporting holes. Similarly, the layer next to the cathode needs to have the functionality of transporting electrons. In many instances, the hole-(electron) transporting layer also acts as the emitting layer. In some instances one layer can perform the combined functions of hole and electron transport and light emission. The individual layers of the organic film may be all polymeric in nature or combinations of films of polymers and films of small molecules deposited by thermal evaporation. It is preferred that the total thickness of the organic film be less than 1000 nanometers (nm). It is more preferred that the total thickness be less than 500 nm. It is most preferred that the total thickness be less than 300 nm. It is preferred that the thickness of the active (light emitting) layer be less than 400 nanometers (nm). It is more preferred that the thickness is in the range of from 40 to 160 nm.

The ITO-glass which serves as the substrate and the anode may be used for coating after the usual cleaning with detergent, organic solvents and UV-ozone treatment. It may also be first coated with a thin layer of a conducting substance to facilitate hole injection. Such substances include copper phthalocyanine, polyaniline and poly(3,4-ethylenedioxythiophene) (PEDT); the last two in their conductive forms by doping with a strong organic acid, e.g., poly(styrenesulfonic acid). It is preferred that the thickness of this layer be 200 nm or less; it is more preferred that the thickness be 100 nm or less.

In the cases where a hole-transporting layer is used, the polymeric arylamines described in U.S. Pat. No. 5,728,801, may be used. Other known hole-conducting polymers, such as polyvinylcarbazole, may also be used. The resistance of this layer to erosion by the solution of the copolymer film which is to be applied next is obviously critical to the successful fabrication of multi-layer devices. The thickness of this layer may be 500 nm or less, preferably 300 nm or less, most preferably 150 nm or less.

In the case where an electron-transporting layer is used, it may be applied either by thermal evaporation of low molecular weight materials or by solution coating of a polymer with a solvent that would not cause significant damage to the underlying film.

Examples of low molecular weight materials include the metal complexes of 8-hydroxyquinoline (as described by Burrows et al. in *Applied Physics Letters*, Vol. 64, pp. 2718-2720 (1994)), metallic complexes of 10-hydroxybenzo(h)quinoline (as described by Hamada et al. in *Chemistry Letters*, pp. 906-906 (1993)), 1,3,4-oxadiazoles (as described by Hamada et al. in *Optoelectronics--Devices and Technologies*, Vol. 7, pp. 83-93 (1992)), 1,3,4-triazoles (as described by Kido et al. in *Chemistry Letters*, pp. 47-48 (1996)), and dicarboximides of perylene (as described by Yoshida et al. in *Applied Physics Letters*, Vol. 69, pp. 734-736 (1996)).

10 Polymeric electron-transporting materials are exemplified by 1,3,4-oxadiazole-containing polymers (as described by Li et al. in *Journal of Chemical Society*, pp. 2211-2212 (1995), by Yang and Pei in *Journal of Applied Physics*, Vol 77, pp. 4807-4809 (1995)), 1,3,4-triazole-containing polymers (as described by Strukelj et al. in *Science*, Vol. 267, pp. 1969-1972 (1995)), quinoxaline-containing polymers (as described by Yamamoto et al. in *Japan Journal of Applied Physics*, Vol. 33, pp. L250-L253 (1994), O'Brien et al. in *Synthetic Metals*, Vol. 76, pp. 105-108 (1996)), and cyano-PPV (as described by Weaver et al. in *Thin Solid Films*, Vol. 273, pp. 39-47 (1996)). The thickness of this layer may be 500 nm or less, preferably 300 nm or less, most preferably 150 nm or less.

20 The metallic cathode may be deposited either by thermal evaporation or by sputtering. The thickness of the cathode may be from 100 nm to 10,000 nm. The preferred metals are calcium, magnesium, indium, and aluminum. Alloys of these metals may also be used. Alloys of aluminum containing 1 to 5 percent of lithium and alloys of magnesium containing at least 80 percent of magnesium are preferred.

25 In a preferred embodiment, the electroluminescent device comprises at least one hole-transporting polymer film and a light-emitting polymer film comprised of the polymer of the invention, arranged between an anode material and a cathode material such that under an applied voltage, holes are injected from the anode material into the hole-transporting polymer film and electrons are injected from the cathode material into the light-emitting polymer films when the device is forward biased, resulting in light emission from the light-emitting layer.

30 In another preferred embodiment, layers of hole-transporting polymers are arranged so that the layer closest to the anode has the lower oxidation potential, with the adjacent layers having progressively higher oxidation potentials. By these methods, electroluminescent devices having relatively high light output per unit voltage may be prepared.

The term "hole-transporting polymer film" as used herein refers to a layer of a film of a polymer which when disposed between two electrodes to which a field is applied and holes are injected from the anode, permits adequate transport of holes into the emitting polymer.

5 Hole-transporting polymers typically are comprised of triarylamine moieties. The term "light-emitting polymer film" as used herein refers to a layer of a film of a polymer whose excited states can relax to the ground state by emitting photons, preferably corresponding to wavelengths in the visible range. The term "anode material" as used herein refers to a semi-transparent, or transparent, conducting film with a work function between 4.5 electron volts

10 (eV) and 5.5 eV. Examples are gold, silver, copper, aluminum, indium, iron, zinc, tin, chromium, titanium, vanadium, cobalt, nickel, lead, manganese, tungsten and the like, metallic alloys such as magnesium/copper, magnesium/silver, magnesium/aluminum, aluminum/indium and the like, semiconductors such as Si, Ge, GaAs and the like, metallic oxides such as indium-tin-oxide ("ITO"), ZnO and the like, metallic compounds such as CuI

15 and the like, and furthermore, electroconducting polymers such polyacetylene, polyaniline, polythiophene, polypyrrole, polyparaphenylene and the like. Oxides and mixed oxides of indium and tin, and gold are preferred. Most preferred is ITO, especially ITO on glass as substrate. The term "cathode material" as used herein refers to a conducting film with a work function between 2.5 eV and 4.5 eV. Examples are alkali metals, earth alkaline metals, group

20 13 elements, silver, and copper as well as alloys or mixtures thereof such as sodium, lithium, potassium, calcium, lithium fluoride (LiF), sodium-potassium alloy, magnesium, magnesium-silver alloy, magnesium-copper alloy, magnesium-aluminum alloy, magnesium-indium alloy, aluminum, aluminum-aluminum oxide alloy, aluminum-lithium alloy, indium, calcium, and materials exemplified in EP-A 499,011, such as electroconducting polymers e.g. polypyrrole,

25 polythiophene, polyaniline, polyacetylene etc. Preferably lithium, calcium, magnesium, indium, silver, aluminum, or blends and alloys of the above are used. In the case of using a metal or a metallic alloy as a material for an electrode, the electrode can be formed also by the vacuum deposition method. In the case of using a metal or a metallic alloy as a material forming an electrode, the electrode can be formed, furthermore, by the chemical plating

30 method (see for example, Handbook of Electrochemistry, pp 383-387, Mazuren, 1985). In the case of using an electroconducting polymer, an electrode can be made by forming it into a film by means of anodic oxidation polymerization method onto a substrate, which is previously provided with an electroconducting coating.

35 As methods for forming said thin films, there are, for example, the vacuum deposition method, the spin-coating method, the casting method, the Langmuir-Blodgett ("LB") method,

the ink jet printing method and the like. Among these methods, the vacuum deposition method, the spin-coating method, the ink jet printing method and the casting method are particularly preferred in view of ease of operation and cost.

- 5 In the case of forming the layers by using the spin-coating method, the casting method and ink jet printing method, the coating can be carried out using a solution prepared by dissolving the composition in a concentration of from 0.0001 to 90% by weight in an appropriate organic solvent such as benzene, toluene, xylene, tetrahydrofurane, methyltetrahydrofurane, N,N-dimethylformamide, dichloromethane, dimethylsulfoxide and the like.

10


The organic EL device of the present invention has significant industrial values since it can be adapted for a flat panel display of an on-wall television set, a flat light-emitting device, a light source for a copying machine or a printer, a light source for a liquid crystal display or counter, a display signboard and a signal light. The polymers and compositions of the

15 present invention can be used in the fields of an organic EL device, a photovoltaic device, an electrophotographic photoreceptor, a photoelectric converter, a solar cell, an image sensor, and the like.

The following examples are included for illustrative purposes only and do not limit the scope

20 of the claims. Unless otherwise stated, all parts and percentages are by weight.

Example 1




25

Bis(1,5-cyclooctadiene)nickel(0) (2.0 g, 7.27 mmol) and 2,2'-bipyridyl (1.14 g, 7.27 mmol) are dissolved in anhydrous toluene (7.0 ml) and stirred at 80°C for 1 hour under an argon atmosphere in the dark. Monomer 1 (0.85 g, 1.82 mmol) and 2,7-dibromo-9,9-dihexylfluorene


(0.89 g, 1.82 mmol) are dissolved in anhydrous toluene (7.0 ml) and purged thoroughly with argon, then added to the solution of Ni complex and stirred at 80°C for 17 hours under argon in the dark. Anhydrous toluene (7.0 ml) is added and the reaction allowed to progress a further 5 hours. Bromobenzene (1 ml, 9.5 mmol) is added and the reaction stirred for a further 2 hours. The reaction mixture is poured into stirred methanol/c.HCl_(aq) (10:1, 600 ml) and the resulting precipitate is stirred for 30 minutes and collected by filtration. The precipitate was redissolved in toluene (80 ml) and the precipitation repeated in acidic methanol. The precipitate is redissolved in chloroform (80 ml) and passed through a plug of silica, then washed through with chloroform (5 × 100mL). The combined chloroform phases are concentrated to ca. 80 ml and precipitated in stirred methanol (600 ml) and stirred for 30 minutes. The polymer is collected by filtration and dried. 0.674 g; 58% recovery of material; $M_w = 650,000$, $P_D = 2.21$.

The polymerisation of Example 1 may be used to produce either high M_w homopolymers or high M_w statistical co-polymers from the following monomer families:

Monomer 1



Monomer 2




Polymer	Ar ₁	Ar ₂	Ar ₃	R ₁₀₁
1	phenyl	4-bromophenyl	4-bromophenyl	n-hexyl
2	phenyl	4-bromophenyl	4'-bromobiphenyl	n-hexyl
3	phenyl	4'-bromobiphenyl	4'-bromobiphenyl	n-hexyl
4	phenyl	4-bromophenyl	4-bromophenyl	n-heptyl
5	phenyl	4-bromophenyl	4'-bromobiphenyl	n-heptyl
6	phenyl	4'-bromobiphenyl	4'-bromobiphenyl	n-heptyl
7	phenyl	4-bromophenyl	4-bromophenyl	n-octyl
8	phenyl	4-bromophenyl	4'-bromobiphenyl	n-octyl
9	phenyl	4'-bromobiphenyl	4'-bromobiphenyl	n-octyl
10	4- ^t butylphenyl	4-bromophenyl	4-bromophenyl	n-hexyl
11	4- ^t butylphenyl	4-bromophenyl	4'-bromobiphenyl	n-hexyl
12	4- ^t butylphenyl	4'-bromobiphenyl	4'-bromobiphenyl	n-hexyl
13	4- ^t butylphenyl	4-bromophenyl	4-bromophenyl	n-heptyl

14	4- ^t butylphenyl	4-bromophenyl	4'bromobiphenyl	n-heptyl
15	4- ^t butylphenyl	4'bromobiphenyl	4'bromobiphenyl	n-heptyl
16	4- ^t butylphenyl	4-bromophenyl	4-bromophenyl	n-octyl
17	4- ^t butylphenyl	4-bromophenyl	4'bromobiphenyl	n-octyl
18	4- ^t butylphenyl	4'bromobiphenyl	4'bromobiphenyl	n-octyl
19	4-hexylphenyl	4-bromophenyl	4-bromophenyl	n-hexyl
20	4-hexylphenyl	4-bromophenyl	4'bromobiphenyl	n-hexyl
21	4-hexylphenyl	4'bromobiphenyl	4'bromobiphenyl	n-hexyl
22	4-hexylphenyl	4-bromophenyl	4-bromophenyl	n-heptyl
23	4-hexylphenyl	4-bromophenyl	4'bromobiphenyl	n-heptyl
24	4-hexylphenyl	4'bromobiphenyl	4'bromobiphenyl	n-heptyl
25	4-hexylphenyl	4-bromophenyl	4-bromophenyl	n-octyl
26	4-hexylphenyl	4-bromophenyl	4'bromobiphenyl	n-octyl
27	4-hexylphenyl	4'bromobiphenyl	4'bromobiphenyl	n-octyl
28	4- ^t butylbiphenyl	4-bromophenyl	4-bromophenyl	n-hexyl
29	4- ^t butylbiphenyl	4-bromophenyl	4'bromobiphenyl	n-hexyl
30	4- ^t butylbiphenyl	4'bromobiphenyl	4'bromobiphenyl	n-hexyl
31	4- ^t butylbiphenyl	4-bromophenyl	4-bromophenyl	n-heptyl
32	4- ^t butylbiphenyl	4-bromophenyl	4'bromobiphenyl	n-heptyl
33	4- ^t butylbiphenyl	4'bromobiphenyl	4'bromobiphenyl	n-heptyl
34	4- ^t butylbiphenyl	4-bromophenyl	4-bromophenyl	n-octyl
35	4- ^t butylbiphenyl	4-bromophenyl	4'bromobiphenyl	n-octyl
36	4- ^t butylbiphenyl	4'bromobiphenyl	4'bromobiphenyl	n-octyl
37	biphenyl	4-bromophenyl	4-bromophenyl	n-hexyl
38	biphenyl	4-bromophenyl	4'bromobiphenyl	n-hexyl
39	biphenyl	4'bromobiphenyl	4'bromobiphenyl	n-hexyl

40	biphenyl	4-bromophenyl	4-bromophenyl	n-heptyl
41	biphenyl	4-bromophenyl	4'bromobiphenyl	n-heptyl
42	biphenyl	4'bromobiphenyl	4'bromobiphenyl	n-heptyl
43	biphenyl	4-bromophenyl	4-bromophenyl	n-octyl
44	biphenyl	4-bromophenyl	4'bromobiphenyl	n-octyl
45	biphenyl	4'bromobiphenyl	4'bromobiphenyl	n-octyl
46	2-naphthyl	4-bromophenyl	4-bromophenyl	n-hexyl
47	2-naphthyl	4-bromophenyl	4'bromobiphenyl	n-hexyl
48	2-naphthyl	4'bromobiphenyl	4'bromobiphenyl	n-hexyl
49	2-naphthyl	4-bromophenyl	4-bromophenyl	n-heptyl
50	2-naphthyl	4-bromophenyl	4'bromobiphenyl	n-heptyl
51	2-naphthyl	4'bromobiphenyl	4'bromobiphenyl	n-heptyl
52	2-naphthyl	4-bromophenyl	4-bromophenyl	n-octyl
53	2-naphthyl	4-bromophenyl	4'bromobiphenyl	n-octyl
54	2-naphthyl	4'bromobiphenyl	4'bromobiphenyl	n-octyl
55	3,4-dibutoxy-phenyl	4-bromophenyl	4-bromophenyl	- ¹⁾
56	3,4-dioktoxy-phenyl	4-bromophenyl	4-bromophenyl	- ¹⁾
57	3,4-didecan-oxyphenyl	4-bromophenyl	4-bromophenyl	- ¹⁾

¹⁾ Homopolymer; no monomer 2.

Example 2




Monomer 1 (1.0 g, 2.15 mmol) and monomer 3 (1.38 g, 2.15 mmol) are suspended in toluene (15 ml) and purged by bubbling argon through for 10 minutes. Palladium catalyst (1 mol%) is added and the toluene phase purged for a further 10 minutes. Tetraethylammonium hydroxide (20% aq. solution; 8 ml) is added and the whole heated to reflux for 20 hours.


- 5 Bromobenzene (0.2 ml) is added and the reaction allowed to proceed for a further hour, then phenylboronic acid added and the reaction stirred for another hour. On cooling the reaction mixture is diluted with toluene (20 ml) and poured into acidic methanol (10 ml 32% $\text{HCl}_{(\text{aq})}$ in 500 ml MeOH) and filtered. The pale solid is redissolved in CHCl_3 (100 ml) and filtered through a plug of silica (3cm), then washed through with CHCl_3 (500 ml). The CHCl_3 is removed and the residue redissolved in toluene (100 ml) and stirred vigorously with an aqueous solution of disodium EDTA (5%, 200 ml) for 1 hour. The toluene phase is separated, concentrated to ca. 50 ml and precipitated in MeOH (400 ml), filtered and dried. 875mg, 79% recovery.
- 10

- 15 The polymerisation of Example 2 may be used to produce alternating copolymers of the following monomer families:

Monomer 1



Monomer 3




Polymer	Ar ₁	Ar ₂	Ar ₃	R ₁₀₁
58	phenyl	4-bromophenyl	4-bromophenyl	n-hexyl
59	phenyl	4-bromophenyl	4'bromobiphenyl	n-hexyl
60	phenyl	4'bromobiphenyl	4'bromobiphenyl	n-hexyl
61	phenyl	4-bromophenyl	4-bromophenyl	n-heptyl
62	phenyl	4-bromophenyl	4'bromobiphenyl	n-heptyl
63	phenyl	4'bromobiphenyl	4'bromobiphenyl	n-heptyl
64	phenyl	4-bromophenyl	4-bromophenyl	n-octyl
65	phenyl	4-bromophenyl	4'bromobiphenyl	n-octyl
66	phenyl	4'bromobiphenyl	4'bromobiphenyl	n-octyl
67	4- ^t butylphenyl	4-bromophenyl	4-bromophenyl	n-hexyl
68	4- ^t butylphenyl	4-bromophenyl	4'bromobiphenyl	n-hexyl
69	4- ^t butylphenyl	4'bromobiphenyl	4'bromobiphenyl	n-hexyl

70	4- ^t butylphenyl	4-bromophenyl	4-bromophenyl	n-heptyl
71	4- ^t butylphenyl	4-bromophenyl	4'-bromobiphenyl	n-heptyl
72	4- ^t butylphenyl	4'-bromobiphenyl	4'-bromobiphenyl	n-heptyl
73	4- ^t butylphenyl	4-bromophenyl	4-bromophenyl	n-octyl
74	4- ^t butylphenyl	4-bromophenyl	4'-bromobiphenyl	n-octyl
75	4- ^t butylphenyl	4'-bromobiphenyl	4'-bromobiphenyl	n-octyl
76	4-hexylphenyl	4-bromophenyl	4-bromophenyl	n-hexyl
77	4-hexylphenyl	4-bromophenyl	4'-bromobiphenyl	n-hexyl
78	4-hexylphenyl	4'-bromobiphenyl	4'-bromobiphenyl	n-hexyl
79	4-hexylphenyl	4-bromophenyl	4-bromophenyl	n-heptyl
80	4-hexylphenyl	4-bromophenyl	4'-bromobiphenyl	n-heptyl
81	4-hexylphenyl	4'-bromobiphenyl	4'-bromobiphenyl	n-heptyl
82	4-hexylphenyl	4-bromophenyl	4-bromophenyl	n-octyl
83	4-hexylphenyl	4-bromophenyl	4'-bromobiphenyl	n-octyl
84	4-hexylphenyl	4'-bromobiphenyl	4'-bromobiphenyl	n-octyl
85	4- ^t butylbiphenyl	4-bromophenyl	4-bromophenyl	n-hexyl
86	4- ^t butylbiphenyl	4-bromophenyl	4'-bromobiphenyl	n-hexyl
87	4- ^t butylbiphenyl	4'-bromobiphenyl	4'-bromobiphenyl	n-hexyl
88	4- ^t butylbiphenyl	4-bromophenyl	4-bromophenyl	n-heptyl
89	4- ^t butylbiphenyl	4-bromophenyl	4'-bromobiphenyl	n-heptyl
90	4- ^t butylbiphenyl	4'-bromobiphenyl	4'-bromobiphenyl	n-heptyl
91	4- ^t butylbiphenyl	4-bromophenyl	4-bromophenyl	n-octyl
92	4- ^t butylbiphenyl	4-bromophenyl	4'-bromobiphenyl	n-octyl
93	4- ^t butylbiphenyl	4'-bromobiphenyl	4'-bromobiphenyl	n-octyl
94	biphenyl	4-bromophenyl	4-bromophenyl	n-hexyl
95	biphenyl	4-bromophenyl	4'-bromobiphenyl	n-hexyl

96	biphenyl	4'bromobiphenyl	4'bromobiphenyl	n-hexyl
97	biphenyl	4-bromophenyl	4-bromophenyl	n-heptyl
98	biphenyl	4-bromophenyl	4'bromobiphenyl	n-heptyl
99	biphenyl	4'bromobiphenyl	4'bromobiphenyl	n-heptyl
100	biphenyl	4-bromophenyl	4-bromophenyl	n-octyl
101	biphenyl	4-bromophenyl	4'bromobiphenyl	n-octyl
102	biphenyl	4'bromobiphenyl	4'bromobiphenyl	n-octyl
103	2-naphthyl	4-bromophenyl	4-bromophenyl	n-hexyl
104	2-naphthyl	4-bromophenyl	4'bromobiphenyl	n-hexyl
105	2-naphthyl	4'bromobiphenyl	4'bromobiphenyl	n-hexyl
106	2-naphthyl	4-bromophenyl	4-bromophenyl	n-heptyl
107	2-naphthyl	4-bromophenyl	4'bromobiphenyl	n-heptyl
108	2-naphthyl	4'bromobiphenyl	4'bromobiphenyl	n-heptyl
109	2-naphthyl	4-bromophenyl	4-bromophenyl	n-octyl
110	2-naphthyl	4-bromophenyl	4'bromobiphenyl	n-octyl
111	2-naphthyl	4'bromobiphenyl	4'bromobiphenyl	n-octyl


Example 3



- 5 Bis(1,5-cyclooctadiene)nickel(0) (2.0 g, 7.27 mmol) and 2,2'-bipyridyl (1.14 g, 7.27 mmol) are dissolved in anhydrous toluene (7.0 ml) and stirred at 80 °C for 1 hour under an argon atmosphere in the dark. Monomer 3 (2.38 g, 3.3 mmol) is dissolved in anhydrous toluene (7.0 ml) and purged thoroughly with argon, then added to the solution of Ni complex and stirred at 80 °C for 17 hours, under argon in the dark. Anhydrous toluene (7.0 ml) is added and the reaction allowed to progress a further 5 hours. Bromobenzene (1 ml, 9.5 mmol) is added and the reaction stirred for a further 2 hours. The reaction mixture is poured into stirred methanol/c.HCl_(aq) (10:1, 600 ml) and the resulting precipitate is stirred for 30 minutes and collected by filtration. The precipitate is redissolved in toluene (80 ml) and the precipitation in acidic methanol repeated. The precipitate is redissolved in chloroform (80 ml)
- 10

and passed through a plug of silica, then washed through with chloroform (5×100 ml). The combined chloroform phases were concentrated to ca. 80 ml and precipitated in stirred methanol (600 ml) and stirred for 30 minutes. The polymer is collected by filtration and dried.

5 Example 4



Monomer 4

Monomer 4 (5.0 g, 14.95 mmol), AIBN (48 mg, 0.293 mmol) and chlorobenzene (12 g) are purged with argon, then heated to 150°C under an argon atmosphere for 2 hours. The hot solution was poured into stirred methanol (300 ml) and the resultant white precipitate filtered.

- 10 The precipitate is redissolved in toluene (60 ml) and slowly dropped into an acidic methanol solution (2 ml c.HCl_(aq) in 400 ml MeOH). The polymer is filtered, washed with methanol and dried at 40°C *in vacuo* overnight. Mass = 3.5 g, 70% recovery of materials; $M_w = 20,000$ (GPC, PS standards).

15 Application Example 1

The ITO-glass used for device fabrication has a nominal sheet resistance of 15 ohm/square.

The hole injection conducting polymer when used is poly(3,4-ethylenedioxy-thiophene) (PEDT), the hole-transporting polymer when used is poly(4,4'-biphenylene-diyl-N,N'-diphenyldiamino-1,4-phenylene) described in US-B-5,728,801, hereinafter abbreviated as

- 20 "P3DA", and the electron-transporting layer when used is the aluminum complex of 8-hydroxy-quinoline hereinafter abbreviated as "Alq". Films of PEDT are formed by spin coating from aqueous solutions of the polymer obtained from Bayer Corporation. Films of P3DA are formed by spin coating from chlorobenzene solutions. Alq films are formed by thermal evaporation in high vacuum. Multi-layer devices are fabricated by laying, down the layers
- 25 sequentially starting from the layer next to the ITO. After all the layers have been deposited, the appropriate metallic cathodes are then deposited on top of the organic film by thermal evaporation. Magnesium alloys in this instance are alloys of magnesium containing at least 85 percent of magnesium.


Electroluminescent Devices:

Device No.	Hole Injection	Hole Transport	Polymer	Electron Transport	Cathode
D1	-	-	64	-	Mg alloy
D2	-	-	64	Alq	"
D3	-	P3DA	64	-	"
D4	-	P3DA	64	Alq	"
D5	PEDT	PVK	64	-	Al


PVK = polyvinylcarbazol

Claims


1. A polymer comprising a repeating unit of the formula




(I), especially




(Ia), or




(Ib); and/ or




(II), especially



(IIa),




(IIb), or




(IIc); wherein

R^1 , R^2 , R^3 , R^4 and R^5 are independently of each other an organic substituent, especially C_2 - C_{30} aryl or a C_2 - C_{26} heteroaryl, which optionally can be substituted, X^1 , X^2 and X^3 are independently of each other a divalent linking group.

2. A polymer according to claim 1, wherein X^1 and X^2 are independently of each other a group of the formula





$n_1, n_2, n_3, n_4, n_5, n_6$ and n_7 are integers of 1 to 10, in particular 1 to 3,

R^6 and R^7 are independently of each other H , C_1 - C_{18} alkyl, C_1 - C_{18} alkyl which is

substituted by E and/or interrupted by D , C_6 - C_{24} aryl, C_6 - C_{24} aryl which is substituted by E , C_2 - C_{20} heteroaryl, C_2 - C_{20} heteroaryl which is substituted by E , C_2 - C_{18} alkenyl, C_2 - C_{18} alkynyl, C_1 - C_{18} alkoxy, C_1 - C_{18} alkoxy which is substituted by E and/or interrupted by D , C_7 - C_{25} aralkyl, or $-CO-R^{28}$,

R^8 is C_1 - C_{18} alkyl, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D , C_6 - C_{24} aryl, or C_7 - C_{25} aralkyl,

R^9 and R^{10} are independently of each other C_1 - C_{18} alkyl, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D , C_6 - C_{24} aryl, C_6 - C_{24} aryl which is substituted by E , C_2 - C_{20} heteroaryl, C_2 - C_{20} heteroaryl which is substituted by E , C_2 - C_{18} alkenyl, C_2 - C_{18} alkynyl, C_1 - C_{18} alkoxy, C_1 - C_{18} alkoxy which is substituted by E and/or interrupted by D , or C_7 - C_{25} aralkyl, or


R^9 and R^{10} form a ring, especially a five- or six-membered ring,

$R^{14'}$ and $R^{15'}$ are independently of each other H , C_1 - C_{18} alkyl, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D , C_6 - C_{24} aryl, C_6 - C_{24} aryl which is substituted by E , C_2 - C_{20} heteroaryl, or C_2 - C_{20} heteroaryl which is substituted by E ,


D is $-CO-$, $-COO-$, $-S-$, $-SO-$, $-SO_2-$, $-O-$, $-NR^{25}-$, $-SiR^{30}R^{31}-$, $-POR^{32}-$, $-CR^{23}=CR^{24}-$, or $-C\equiv C-$, and

E is $-OR^{29}$, $-SR^{29}$, $-NR^{25}R^{26}$, $-COR^{28}$, $-COOR^{27}$, $-CONR^{25}R^{26}$, $-CN$, $-OCOOR^{27}$, or halogen, wherein

R^{23} , R^{24} , R^{25} and R^{26} are independently of each other H , C_6 - C_{18} aryl, C_6 - C_{18} aryl which is substituted by C_1 - C_{18} alkyl, C_1 - C_{18} alkoxy, C_1 - C_{18} alkyl, or C_1 - C_{18} alkyl which is interrupted by $-O-$, or



R^{25} and R^{26} together form a five or six membered ring, in particular




R^{27} and R^{28} are independently of each other H, C_6-C_{18} aryl, C_6-C_{18} aryl which is substituted by C_1-C_{18} alkyl, or C_1-C_{18} alkoxy, C_1-C_{18} alkyl, or C_1-C_{18} alkyl which is interrupted by $-O-$,


R^{29} is H, C_6-C_{18} aryl, C_6-C_{18} aryl, which is substituted by C_1-C_{18} alkyl, C_1-C_{18} alkoxy, C_1-C_{18} alkyl, or C_1-C_{18} alkyl which is interrupted by $-O-$,

R^{30} and R^{31} are independently of each other C_1-C_{18} alkyl, C_6-C_{18} aryl, or C_6-C_{18} aryl, which is substituted by C_1-C_{18} alkyl, and

R^{32} is C_1-C_{18} alkyl, C_6-C_{18} aryl, or C_6-C_{18} aryl, which is substituted by C_1-C_{18} alkyl.

3. A polymer according claim 1 or 2, wherein R^1 and R^2 are independently of each other H, C_1-C_{18} alkyl, C_1-C_{18} alkyl which is substituted by E and/or interrupted by D, C_2-C_{18} alkenyl, C_2-C_{18} alkynyl, C_1-C_{18} alkoxy, C_1-C_{18} alkoxy which is substituted by E and/or interrupted by D, C_7-C_{25} aralkyl, C_6-C_{24} aryl or C_2-C_{20} heteroaryl, which optionally can be substituted, especially a group of the formula








5


R¹¹, R¹² and R¹³ are independently of each other H, C₁-C₁₈ alkyl, C₁-C₁₈alkyl which is substituted by E and/or interrupted by D, C₆-C₂₄aryl, C₆-C₂₄aryl which is substituted by E, C₂-C₁₈alkenyl, C₂-C₁₈alkynyl, C₁-C₁₈alkoxy, C₁-C₁₈alkoxy which is substituted by E and/or interrupted by D, or C₇-C₂₅aralkyl, and

10

D, E, R⁶, R⁷, R⁸, R⁹, R¹⁰, R^{14'} and R^{15'} are as defined in claim 2.

- 4.






R^{16} is H, C_6-C_{18} aryl, C_6-C_{18} aryl which is substituted by C_1-C_{18} alkyl, C_1-C_{18} alkyl, C_6-C_{24} aryl, which can optionally be substituted, or C_1-C_{18} alkyl which is interrupted by $-O-$,
 p is an integer from 1 to 10, especially 1, 2 or 3,
 q is an integer from 1 to 10, especially 1, 2 or 3,
 s is an integer from 1 to 10, especially 1, 2 or 3,
 R^6 , R^7 , R^8 , R^9 and R^{10} are as defined in claim 2, or

R^9 and R^{10} together form a group of formula $=CR^{100}R^{101}$, wherein R^{100} and R^{101} are independently of each other H, C_1 - C_{18} alkyl, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D, C_6 - C_{24} aryl, C_6 - C_{24} aryl which is substituted by E, or C_2 - C_{20} heteroaryl, or C_2 - C_{20} heteroaryl which is substituted by E, and R^{14} and R^{15} are independently of each other H, C_1 - C_{18} alkyl, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D, C_6 - C_{24} aryl, C_6 - C_{24} aryl which is substituted by E, or C_2 - C_{20} heteroaryl, C_2 - C_{20} heteroaryl which is substituted by E.

5. A polymer according to any of claims 1 to 3, comprising repeating units of formula Ia or Ib, wherein R^1 is a group of formula



wherein R^2 is H,

R^6 and R^7 are independently of each other H, C_1 - C_{12} alkyl, C_6 - C_{24} aryl, especially phenyl, naphthyl, or biphenyl, which can be substituted by $-O$ - C_1 - C_{12} alkyl, or C_1 - C_{18} alkoxy,


R^9 and R^{10} are independently of each other H, C_1 - C_{12} alkyl, or C_1 - C_{12} alkoxy,

R^8 is C_1 - C_{18} alkyl, C_1 - C_{18} alkyl interrupted by one or two oxygen atoms, or C_6 - C_{12} aryl, which optionally can be substituted by C_1 - C_{12} alkyl, or C_1 - C_{12} alkoxy,

R^9 and R^{10} are independently of each other C_1 - C_{18} alkyl, especially C_4 - C_{12} alkyl, which can be interrupted by one or two oxygen atoms, and X^1 and X^2 are as defined in claim 1.

6. A polymer according to claim 5, comprising a co-monomer T which is selected from the group consisting of






R^9 and R^{10} are independently of each other C_1 - C_{18} alkyl, especially C_4 - C_{12} alkyl, which can be interrupted by one or two oxygen atoms, or

R^9 and R^{10} form a five or six membered carbocyclic ring, which optionally can be substituted by C_1 - C_4 alkyl, and

R^8 is C_1 - C_{18} alkyl.


- 10 7. A polymer according to claim 1, comprising a repeating unit of formula




a co-monomer $\left[\text{T} \right]_y$, wherein

x is in the range of 0.005 to 1, especially 0.4 to 0.6, and y is in the range of 0.995 to 0, especially 0.6 to 0.4, wherein the sum of x and y is 1,

R¹ is a group of formula



especially





wherein X⁶ is H, C₁-C₁₈alkyl, or C₁-C₁₈alkoxy,


R² is H,

5


X¹ and X² are independently of each other a group of formula




, especially



, or



, and



T is a group of formula

, wherein s is one or two, and R⁹ and

R¹⁰ are independently of each other C₁-C₁₈alkyl, especially C₄-C₁₂alkyl, which can be interrupted by one or two oxygen atoms, and



10

R⁶ and R⁷ are independently of each other H, C₁-C₁₂alkyl, C₆-C₂₄aryl, especially phenyl, naphthyl, or biphenyl, which can be substituted by -O-C₁-C₁₂alkyl, or C₁-C₁₈alkoxy.


8. A polymer according to claim 1, comprising a repeating unit having the formula IIa, IIb

15



or IIc, wherein X³ is a group of the formula




, or



; especially





, wherein the dotted line represent the bond to the

pyrimidine ring,

R^3 , R^4 and R^5 are as defined in claim 1,

R^{56} and R^{57} are independently of each other H, C_1 - C_{18} alkyl, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D, C_6 - C_{24} aryl, C_6 - C_{24} aryl which is substituted by E, C_2 - C_{20} heteroaryl, C_2 - C_{20} heteroaryl which is substituted by E, C_2 - C_{18} alkenyl, C_2 - C_{18} alkynyl, C_1 - C_{18} alkoxy, C_1 - C_{18} alkoxy which is substituted by E and/or interrupted by D, or C_7 - C_{25} aralkyl,

R^{58} is H, C_1 - C_{18} alkyl, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D, C_6 - C_{24} aryl, or C_7 - C_{25} aralkyl,


R^{59} and R^{60} are independently of each other H, C_1 - C_{18} alkyl, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D, C_6 - C_{24} aryl, C_6 - C_{24} aryl which is substituted by E, C_2 - C_{20} heteroaryl, C_2 - C_{20} heteroaryl which is substituted by E, C_2 - C_{18} alkenyl, C_2 - C_{18} alkynyl, C_1 - C_{18} alkoxy, C_1 - C_{18} alkoxy which is substituted by E and/or interrupted by D, or C_7 - C_{25} aralkyl, or

R^{59} and R^{60} form a ring, especially a five- or six-membered ring,


D is $-CO-$; $-COO-$; $-OCOO-$; $-S-$; $-SO-$; $-SO_2-$; $-O-$; $-NR^{25}-$; $-SiR^{30}R^{31}-$; $-POR^{32}-$; $-CR^{23}=CR^{24}-$; or $-C\equiv C-$; and

E is $-OR^{29}$; $-SR^{29}$; $-NR^{25}R^{26}$; $-COR^{28}$; $-COOR^{27}$; $-CONR^{25}R^{26}$; $-CN$; $-OCOOR^{27}$; or halogen; wherein

R^{23} , R^{24} , R^{25} and R^{26} are independently of each other H; C_6 - C_{18} aryl; C_6 - C_{18} aryl which is substituted by C_1 - C_{18} alkyl, C_1 - C_{18} alkoxy; C_1 - C_{18} alkyl; or C_1 - C_{18} alkyl which is interrupted by $-O-$; or





R^{25} and R^{26} together form a five or six membered ring, in particular



10


- 15






5

wherein m_1 , m_2 , m_3 , m_4 , m_5 , m_6 and m_7 are integers of 1 to 10, in particular 1 to 3, X^6 is H, C_1 - C_{18} alkyl, C_1 - C_{18} alkoxy, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D, C_6 - C_{24} aryl, which can optionally be substituted,



especially

which can optionally be substituted, especially



10

, C_2 - C_{18} alkenyl, C_2 - C_{18} alkynyl, C_1 - C_{18} alkoxy, C_1 - C_{18} alkoxy which is substituted by E and/or interrupted by D, or C_7 - C_{25} aralkyl,

X^4 is C_1 - C_{18} alkyl, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D, C_6 - C_{24} aryl or C_2 - C_{20} heteroaryl, which can optionally be substituted,


X^5 is C_1 - C_{18} alkyl, C_6 - C_{24} aryl, or C_2 - C_{20} heteroaryl, which can optionally be substituted by - OC_1 - C_{18} alkyl or - OC_6 - C_{24} aryl,

15

5 R^{64} and R^{65} are independently of each other H, C_1 - C_{18} alkyl, C_1 - C_{18} alkyl which is substituted by E and/or interrupted by D, C_6 - C_{24} aryl, C_6 - C_{24} aryl which is substituted by E, or C_2 - C_{20} heteroaryl, C_2 - C_{20} heteroaryl which is substituted by E, and D, E, R^{56} , R^{57} , R^{58} , R^{59} and R^{60} are as defined in claim 8.

10





5 wherein p is an integer from 1 to 10, especially 1, 2 or 3,

q is an integer from 1 to 10, especially 1, 2 or 3,

s is an integer from 1 to 10, especially 1, 2 or 3,

p is an integer from 1 to 10, especially 1, 2 or 3,


10 R^{72} is H, C_6-C_{18} aryl, C_6-C_{18} aryl, which is substituted by C_1-C_{18} alkyl, C_1-C_{18} alkoxy; C_1-C_{18} alkyl; or C_1-C_{18} alkyl which is interrupted by $-O-$;


R^{56} , R^{57} , R^{58} , R^{59} , R^{60} , R^{64} and R^{65} are as defined in claim 8, or

R^{59} and R^{60} together form a group of formula $=CR^{100}R^{101}$, wherein

15 R^{100} and R^{101} are independently of each other H, C_1-C_{18} alkyl, C_1-C_{18} alkyl which is substituted by E and/or interrupted by D, C_6-C_{24} aryl, C_6-C_{24} aryl which is substituted by E, or C_2-C_{20} heteroaryl, or C_2-C_{20} heteroaryl which is substituted by E.





11. A polymer according to any of claims 8 to 10, comprising a repeating unit of formula IIb, especially a repeating unit of formula IIa, or IIc, and a co-monomer T, wherein





X^3 is a group of the formula , wherein the dotted line represent the bond to the pyrimidine ring and R^{71} is H, alkyl, $-C\equiv N$, or $-COOR^{27}$, wherein R^{27} is H, or C_1 - C_{18} alkyl; which optionally can be interrupted by one or more oxygen atoms, especially C_4 - C_{12} alkyl, which can be interrupted by one or two oxygen atoms,

5

R^3 , R^4 , and R^5 are independently of each other H,



T is a group of formula



, or
each other C_1 - C_{18} alkyl, especially C_4 - C_{12} alkyl, which can be interrupted by one or two oxygen atoms.

10

12. An optical device or a component therefore, comprising a substrate and a polymer according to any of claims 1 to 11.

15

13. An optical device according to claim 12, wherein the optical device comprises an electroluminescent device.

14. An optical device according to claim 13, wherein the electroluminescent device comprises


20

- (a) a charge injecting layer for injecting positive charge carriers,
- (b) a charge injecting layer for injecting negative charge carriers,




(c) a light-emissive layer located between the layers (a) and (b) comprising a polymer according to any of claims 1 to 11.

15. A monomer of the formula



5




(III), especially



(IV), especially




(IVb), or



wherein

10

R^1 , R^2 , R^3 , R^4 and R^5 are independently of each other an organic substituent, especially a C_2 - C_{30} aryl or a C_2 - C_{26} heteroaryl, which optionally can be substituted, X^1 , X^2 , and X^3 are independently of each other a divalent linking group, and X^{11} is independently in each occurrence a halogen atom, or $-B(OH)_2$, $-B(OY^1)_2$ or



, wherein Y^1 is independently in each occurrence a C_1 - C_{10} alkyl group and

15

Y^2 is independently in each occurrence a C_2 - C_{10} alkylene group, such as $-CY^3Y^4-CY^5Y^6-$, or $-CY^7Y^8-CY^9Y^{10}-CY^{11}Y^{12}-$, wherein Y^3 , Y^4 , Y^5 , Y^6 , Y^7 , Y^8 , Y^9 , Y^{10} , Y^{11} and Y^{12} are independently of each other hydrogen, or a C_1 - C_{10} alkyl group, especially $-C(CH_3)_2C(CH_3)_2-$, or $-C(CH_3)_2CH_2C(CH_3)_2-$.

Abstract:

5 The present invention relates to polymers comprising diazine, especially pyrimidine, containing repeating units. Optical devices, comprising the polymers of the present invention, can show significant advantages in color purity, device efficiency and/or operational lifetime. In addition, the polymers can have good solubility characteristics and relatively high glass transition temperatures, which facilitates their fabrication into coatings and films that are relatively thin, thermally stable, and relatively free of defects.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☒ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.